

Diversey™

Bona SuperCourt® Poly 350

Oil Modified Wood Floor Finish

Polyurethane 350 is a high gloss oil modified urethane finish formulated for one coat application on wood sports floors.

Features & Benefits

- Tough, high gloss finish with light amber color enhances the natural color of the wood floor
- Provides outstanding resistance from soil, perspiration, heavy traffic and daily cleaning
- Formulated without APEOs, NMPs or phosphates
- Maximum VOC content of 350 g/L
- Manufactured by Bona solely for Diversey

Applications

- For use on unsealed wood sport floors. Not intended for use on stone, resilient or rubber flooring
- Can be used over most waterbased and oil modified finishes after proper preparation, drying and curing times
- Designed to work in conjunction with: Bona SuperCourt® Cleaner Concentrate and Prominence™/MC Heavy Duty Floor Cleaner
- Applies flawlessly with Bona SuperCourt® Athletic Floor Care System



Wood Care by Diversey
Powered by Bona



Bona SuperCourt® Poly 350

Oil Modified Wood Floor Finish

Use instructions

RECOATING: 1. Evaluate the Floor – Evaluate the entire wood floor for scuff marks, current finish condition/peeling, cupping and other damage, and overall floor appearance. **2. Prepare the floor** – Gather all recommended tools and materials for the job. Secure the work area and post signs on entrance doors with “Do Not Enter.” Use the Bona SuperCourt Microfiber Dusting Pad to dry dust the floor. Remove tape/sticky spots from the floor by cleaning with an auto scrubber and SuperCourt AFC Microfiber Cleaning Pads and Bona SuperCourt Cleaner Concentrate. Let dry. **3. Abrasion** – Once the floor has dried, abrade the floor using the Bona FlexiSand DCS Buffer and Bona DCS Back Vac with 180-grit Bona Diamond abrasives on a Bona MultiDisc. Abrade the entire work area. Work in sections, making sure to overlap sections. (Bona Diamond abrasives will last 4000-6000 square feet before replacement.) **4. Post-abrasion cleaning** – Vacuum and dry tack the entire floor to remove abrasive dust. Auto scrub or wet tack entire floor. **5. Coating preparation** – Before coating, tape-off floor plates, outlets, and areas needing protection from the floor finish. Strain finish and pour into clean dispensing container, or work from pail. Clean and rinse applicators. Place finish every 3250 square feet to assist with coverage rate. Have an exit strategy. For more information, and to watch a video on the recoat process: visit www.Bona.com.

RECOMMENDED APPLICATORS: Brush, lambswool applicator, heavyweight t-bar and Bona Floor Coater Sleeve. NOTE: Use a clean applicator for sealer and a separate clean applicator for finish.

MIXING INSTRUCTIONS: Remove lid and stir thoroughly before using. DO NOT THIN.

FINISHING: 1. Pour a 4” – 6” wide line of finish along the starting wall. Go with the grain of the wood, applying a thin, uniform coat. **2.** Using a Bona Floor Coater Sleeve on a heavyweight t-bar, draw the applicator forward with the grain of the wood, moving the finish toward the opposite wall. Hold the applicator at a “snowplow” angle. **3.** Avoid leaving puddles or excessive amounts of finish on the floor. **4. BE SURE YOU ARE USING THE RECOMMENDED COVERAGE OF 600-650 SQUARE FEET PER GALLON.** **5.** Allow first coat to dry thoroughly (approximately 18-24 hours). High humidity and/or low temperature conditions will extend the dry time (recommended conditions of 65-80°F/40-60% relative humidity). **6.** For proper adhesion, abrade between all coats of finish. **7.** Allow final coat to dry at least 72 hours before use.

INTERCOAT ABRASION: Abrade between all oil-modified sealer and finish coats using 180 or 240-grit Bona Diamond abrasives mounted on 1-2 Bona Conditioning Pads. As an alternative when abrading between coats of finish, use a Bona MultiDisc with 180 or 240-grit Bona Diamond abrasives. Always vacuum and tack thoroughly after abrading. Apply finish coat within 24 hours.

CURING: The curing process takes approximately 14 days. The floor may be walked on after 24 hours, but the floor is susceptible to scuffing or marring prior to completion of the curing time. Do not replace athletic or walk-off mats until finish is fully cured. Do not clean with water or detergent during the curing process.

Technical data	Bona SuperCourt® Poly 350
Certifications	MFMA
Color/Form	Amber liquid
pH	NA (RTU)
Scent	Solvent
Shelf Life	1 year

Product	Pack size	Product code
Bona SuperCourt® Poly 350	1 x 5 gallon / 18.9 L Container	101101771 

Safe handling

Please make sure your employees read and understand the product label and Safety Data Sheet before using this product. The label contains directions for use; and both the label and SDS contain hazard warnings, precautionary statements and first aid procedures. SDS are available online at www.diversey.com or by calling 888.352.2249. Improper use or dilution may result in damage to surfaces and may result in health and physical hazards that match those of the concentrate.