



A seal and finish. Seal 340 was formulated to enhance the rich, natural colors of your hard floors without leaving a shiny, plastic-looking surface. It also seals resilient tile floors to create a smooth, unbroken base for high-speed finishes. Seal 340 not only enhances the natural colors in hard floors, it protects all floors from dirt, spills, and abrasions that come from heavy traffic.

Features & Benefits

- Enhances the rich, natural colors of your hard floors
- Protects floors from dirt, spills, and abrasions
- Formulated to dry fast (less than one hour)

Item Number & Unit of Measure

Item Number	HIL0034007
Unit of Measure	5 gal BIB

Specifications

Color	White
Appearance	Milky Emulsion
Fragrance	Non-Objectionable
Formula Type	Liquid
Dilution Ratio	RTU
PH	8.50 - 9.50

Non-Volatile Matter	20.0%
Solids Content	20.0%
Coverage SqFt/Gallon	1500-2000
Dry Time (hrs.)	1
Sheen	Gloss
UL Certified	Yes

Safety

See safety datasheet (if applicable) and product label for safety information, handling and proper use.

Directions for Use

Preparation: New floors: For hard floors, allow surfaces to set 30 days to ensure proper curing of Portland terrazzo or grout joints; for resilient flooring, ensure the adhesive has cured for at least 2 weeks. Scrub with a solution of Hillyard Recoat Prep or Assurance, following label directions, and a blue pad. Pick up scrubbing solution with an automatic scrubber or wet vacuum. Flood rinse with a solution of Hillyard Nutra-Rinse and pick up solution with an automatic scrubber or wet vacuum. Damp mop rinse twice with water and allow to dry for at least 1 hour. **Scrub and recoat:** Scrub the existing floor polish with a solution of Hillyard Recoat Prep or Assurance, following label directions, and a blue pad. Pick up scrubbing solution with an automatic scrubber or wet vacuum. Flood rinse with a solution of Hillyard Nutra-Rinse and pick up solution with an automatic scrubber or wet vacuum. Damp mop rinse twice with water and allow to dry for at least 1 hour. **Stripping:** Strip Seal 340 or other polishes from the floor with a solution of Hillyard Arsenal Stripper, Devastator, or Power-Strip, following label directions. Pick up scrubbing solution with an automatic scrubber or wet vacuum. Flood rinse with a solution of Hillyard Nutra-Rinse and pick up solution with an automatic scrubber or wet vacuum. Damp mop rinse twice with water and allow to dry for at least 1 hour. **Synthetic Sports Floors:** Always check with the flooring manufacturer's warranty concerning the use of

Seal 340 Seal Finish (continued)



maintenance products on your floor. Once warranty has expired or, at your discretion, you decide to use Seal 340, follow the preparation directions on the Hillyard Salvation label. **Application:** When used as a seal, apply a minimum of 2 coats of Seal 340 at a rate of 1500-2000 ft²/gallon with a microfiber flat finish mop or Multi-Flo XP. Allow each coat to dry a minimum of 30 minutes to 1 hour before applying the next. When used as a seal/finish, apply a minimum of 6 coats of Seal 340. **NOTE:** Allow for longer dry time between coats of finish if the humidity is above 80% or the floor temperature is below 60°F (16 °C). For best results, do not apply more than 3-4 coats per day. **Maintenance:** Use a cotton dust mop, treated with Hillyard Super Hil-Tone, daily to remove loose dirt and grit. Damp mop or autoscrub, as scheduled, with Hillyard Super Shine-All®, Top Clean®, or Arsenal® Heavy Duty Floor Cleaner. Scrub and recoat, as scheduled, with a minimum of 2 coats of Seal 340. **FLOOR PAD RECOMMENDATIONS:** **Stripping:** black; **Scrub and Recoat:** blue; **Autoscrubbing:** red. **NOTICE:** Do not use an ammoniated cleaner for daily care. Do not pour unused seal back into the original container.