



A clear waterborne finish for wood sports floors. Requires Pro 200 Crosslinker, HIL0075637 to be ordered and used in conjunction with.

Features & Benefits

- 2-part crosslinked waterborne gym finish
- Ultra-clear
- Exceptional durability
- Up to 24 hours between coats without abrasion

Item Number & Unit of Measure

Item Number	HIL0075507
Unit of Measure	5 gal Pail

Specifications

Color	White
Appearance	Milky Emulsion
Fragrance	Non-Objectionable
Formula Type	Liquid
Dilution Ratio	RTU
PH	8.00 - 9.00
Non-Volatile Matter	26.5 - 28.5%
Solids Content	27
Coverage SqFt/Gallon	500-600
Dry Time (hrs.)	6

Sheen	Gloss
-------	-------

Safety

See safety datasheet (if applicable) and product label for safety information, handling and proper use.

Directions for Use

PREPARATION: NEW OR FRESHLY SANDED

WOOD: After the floor has been properly sanded and screened, tack the entire floor with Pro Spirits. Allow the floor to dry a minimum of one hour. Pro 200 Gym Finish is not intended to be used as a seal on newly sanded or newly installed floors. Use Hillyard Pro Primer II, Pro Sanding Seal, or Pro Seal when a water based seal is required. **SCRUB AND RE-COAT:** Floor can be scrubbed and coated the same day. Scrub with Court Prep diluted 1:4 using Trident® Multi-Finish Prep Pads (MFPP) (250-500 ft² per side). under a single brush floor machine (use a white pad between the pad holder and the disc). Pick up the solution with a wet vacuum and damp mop rinse twice with clean water. Work small areas and do not flood floor. Allow the floor to dry one hour. Tack the floor with terry cloth towels dampened with Court Tack or Court Prep. Allow floor to dry at least 30 minutes. If you choose to dry screen, be sure to sweep, vacuum, and tack until the floor is completely dust free. **MIXING**

INSTRUCTIONS: Open crosslinker and add equal volume of water to the crosslinker and shake well. Add the crosslinker/water mixture to finish within 15 minutes. Mix finish as crosslinker/water mixture is added and let stand for 5-10 minutes before applying. Pot Life: The finish/crosslinker mixture is active for approximately 8 hours. **APPLICATION:** Before applying Pro 200 Gym Finish, tack the floor a final time with a cleaning cloth similar to Hillyard Item CHI415. Apply at a coverage rate of 500-700 square feet per gallon using approved applicator (see below). Two coats of Pro 200 Gym Finish are recommended for re-coating floors. Avoid leaving puddles of finish on the floor. Allow first coat to dry at least 3-5 hours, abrading between coats is not required unless

finish has dried for 24 hours or longer. If Pro 200 dries longer than 24 hours abrade with maroon pads (250 sq. ft. per side of pad), and tack with Court Tack or Court Prep. If Pro 200 Gym Finish dries longer than 48 hours, abrade with MFPP (250 ft² per side). Apply the second coat of Pro 200 Gym Finish in the same manner. Do not use floor for at least 72 hours and wait one week for scheduled activities. **Note: Turn on the exhaust system two to four hours after each application of Pro 200 Gym Finish. If after abrading, the floor sits for longer than 24 hours before being coated, re-abrade and tack before applying additional finish coats to prevent peeling from occurring. Under normal drying conditions, allow the floor to cure 24 hours before opening to light traffic; allow 72 hours before scheduling normal activities.****CLEAN-UP:** Use warm water to clean application equipment. **APPROVED APPLICATORS:** Hillyard Multi-Flo[®] and lightweight T-Bar with synthetic pad.

IMPORTANT: Prior to recoating, if game lines need to be touched up, use Hillyard approved paint following label directions. Worn areas should be patched in with Pro 200 Gym Finish prior to re-coating the entire floor. **NOTE:** For wood substrates only. **NOTE:** Best results are obtained with adequate ventilation and floor temperature above 60° F (16°C). Temperature and humidity affect curing properties; low humidity may cause the coating to dry too quickly. Floor temperature should be between 60° and 95° F. During the drying process, avoid direct drafts on floor. Do not use cleaners on Pro 200 Gym Finish until coating has cured one week. **On newer floors be cautious not to flood expansion joints with excess seal and finish.** Keep container closed when not in use. Do not pour unused finish back into container. **NOTICE: Saw dust from freshly sanded floors or dust from wood floors that have been abraded between coats will spontaneously catch fire if improperly discarded. Immediately after abrading or sanding wood floors, place dust waste in a sealed, water-filled metal container and**

immediately remove from building.

NOTICE: Rags or applicators soaked in a combustible liquid will spontaneously catch fire if improperly discarded. Immediately after using rags or applicators soaked in a combustible liquid, place waste in a sealed, water-filled metal container and immediately remove from building.