

Test Report No.: T52510330555TC Date: AUG 15, 2025 Page 1 of 8

BLOOMINGVILLE A/S

LENE HAUS VEJ 3-5 DK-7430 IKAST DENMARK

The following samples were submitted and identified by/on behalf of the client as:

BOLIVIA CUP, BLACK, STONEWARE

Item No. : 82063178 P.O. No. : 70271

Buyer : BLOOMINGVILLE A/S

Country of Origin : CHINA

Country of Destination : DENMARK

Sample Receiving Date : AUG 07, 2025

Testing Period : AUG 07, 2025 TO AUG 15, 2025





Test Report No.: T52510330555TC Date: AUG 15, 2025 Page 2 of 8

Test	Conclusion	
1.	Danish Ordinance on materials and articles intended for food contact (BEK nr 681 of 25 May 2020) – Leachable Lead and Cadmium	PASS
2.	The EC Regulation 1935/2004/EC and the European Council Directive 84/500/EEC and its amendment 2005/31/EC— Ceramic Articles intended to Come into Contact with Foodstuffs - migration Lead and Cadmium	PASS
3.	Norwegian Regulations 1993-12-21 nr 1381 –Forskrift om materialer og gjenstander i kontakt med næringsmidler (matemballasjeforskriften) Kapittel VI and Vedlegg III – Leachable Lead, Cadmium and Barium	PASS

******* FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) *******

Signed for and on behalf of SGS-CSTC Standards Technical Services Co., Ltd. Shenzhen Branch Testing Center

Xue Na, Ella Senior Engineer







Test Report No.: T52510330555TC Date: AUG 15, 2025 Page 3 of 8

Results:

<u>Danish Ordinance on materials and articles intended for food contact (BEK nr 681 of 25 May 2020) – Leachable Lead and Cadmium</u>

Method: With reference to Danish Ordinance on materials and articles intended for food contact (BEK nr BEK nr 681 of 25 May 2020). Analysis was performed by Atomic Absorption Spectrometry.

Toot Itom	Results		Reporting	Category 2
Test Item	1	2	Limit	Limit
Released Lead (mg/L)	ND	ND	0.1	4.0
Released Cadmium (mg/L)	ND	ND	0.01	0.3
Volume of 4% Acetic acid used (mL)	360	360		
Depth (mm)	73	73		
Diameter (mm)	90	90		
Comment	PASS	PASS		

Sample Description:

- 1. Glazed cream ceramic cup w/ dark green pattern
- 2. Glazed dark blue ceramic cup w/ cream pattern

Note: 1. mg/L = milligram per liter

2. ND = Not Detected

Remark: 1. Category 1:

- a. Articles which cannot be filled.
- b. Articles for filling, whose internal depth measured between the lowest point and the upper edge horizontal level is not more than 25 mm.
- c. Articles intended to drink of (Lip & rim region).
- 2. Category 2: Articles, not in categories 1 or 3, which can be filled.
- 3. Category 3:
 - a. Cooking ware
 - b. Packaging and storage vessels having a capacity of more than three litres.
- 4. Drinking rim: The drinking rim is the 20mm wide section, measured downwards from the upper edge along the wall of the vessel, of the external surface of a drinking vessel.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.spx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Condit

1443, or email: Un. Doccneck@sgs.com #monifold(Pant & Royn II) Pant 2 & Royn II) Pant 2 & Royn III Pant 2 を Royn III P



Test Report No.: T52510330555TC Date: AUG 15, 2025 Page 4 of 8

For Drinking Rim:

Test Item	Results		Reporting	Drinking
restitem	1	2	Limit	Rim Limit
Released Lead (mg/dm²)	ND	ND	0.1	0.8
Released Cadmium (mg/dm²)	ND	ND	0.01	0.07
Surface Area (dm²)	1.13	1.13		
Volume of 4% Acetic acid used (mL)	150	150		
Depth (mm)	73	73		
Diameter (mm)	90	90		
Comment	PASS	PASS		

Sample Description:

- 1. Glazed cream ceramic cup w/ dark green pattern
- 2. Glazed dark blue ceramic cup w/ cream pattern

Note: 1. $mg/dm^2 = milligram per square decimeter$

2. ND = Not Detected

Remark: 1. Category 1:

a. Articles which cannot be filled.

- b. Articles for filling, whose internal depth measured between the lowest point and the upper edge horizontal level is not more than 25 mm.
- c. Articles intended to drink of (Lip & rim region).
- 2. Category 2: Articles, not in categories 1 or 3, which can be filled.
- 3. Category 3:
 - a. Cooking ware
 - b. Packaging and storage vessels having a capacity of more than three litres.
- 4. Drinking rim: The drinking rim is the 20mm wide section, measured downwards from the upper edge along the wall of the vessel, of the external surface of a drinking vessel.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Conditions/Terms-and-Comment-Service-Propositions-Propositions-Propositions-Propositions-Propositions-Propositions-India



Test Report No.: T52510330555TC Date: AUG 15, 2025 Page 5 of 8

84/500/EEC and its Amendments 2005/31/EC - Extractable Lead and Cadmium

Method: With reference to Annex I of Council Directive 84/500/EEC and Annex I & Annex II of Commission Directive 2005/31/EC

Analysis was performed by Atomic Absorption Spectrometer (AAS)

Specimen No.1	Trial A	Category 2 Limit
Extractable Lead (mg/L)	< 0.10	4.0
Extractable Cadmium (mg/L)	< 0.02	0.3
Depth (mm)	73	
Diameter (mm)	90	
Volume of 4% Acetic Acid used (ml)	360	

Specimen No.2	Trial A	Category 2 Limit
Extractable Lead (mg/L)	< 0.10	4.0
Extractable Cadmium (mg/L)	< 0.02	0.3
Depth (mm)	73	1
Diameter (mm)	90	1
Volume of 4% Acetic Acid used (ml)	360	

Specimen Description:

- Glazed cream ceramic cup w/ dark green pattern
- 2. Glazed dark blue ceramic cup w/ cream pattern

Note: - mg/L = milligram per liter

- mm = millimeter
- ml = milliliter
- < = less than</p>
- According to 84/500/EEC and EN 1388-2:1995 and DGCCRF MCDA n°2 (V01 01/05/2016), if the
 result of the first tested article does not exceed the limit by more than 150%, three more identical
 articles can be tested. The final result is passed if the average result does not exceed the limit with
 none of the articles exceeding the limit by more than 50%.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Conditions/Terms-and-Comment-Service-Propositions-Propositions-Propositions-Propositions-Propositions-Propositions-India

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 8307
1443, or email: CN.Doccheck@egs.com
Rom IIIV4M; Ran 14 8 Rom III, Plant 13 Rom 101, Plant 13 Rom 10



Test Report No.: T52510330555TC Date: AUG 15, 2025 Page 6 of 8

Ceramic article intended to contact with foodstuff is classified as below table according to 84/500/EEC

Category 1	Articles which cannot be filled and articles which can be filled, the internal depth of which measured from the lowest point to the horizontal plane passing through the upper rim, does not exceed 25mm.
Category 2	All other articles which can be filled
Category 3	Cooking ware; packaging and storage vessels having a capacity of more than 3 liters

Norwegian Regulations 1993-12-21 nr 1381 – Forskrift om materialer og gjenstander i kontakt med næringsmidler (matemballasjeforskriften) Kapittel VI and Vedlegg III – Leachable Lead, Cadmium and Barium

Method: With reference to Norwegian regulation FOR 1993-12-21 nr 1381 section 26. Analysis was performed by Atomic Absorption Spectrometry / Inductively coupled plasma-mass spectrometry (ICP-MS).

Test Item	Results		Reporting	Hollowware
Test item	1	2	Limit	Limit
Released Lead (mg/L)	ND	ND	0.05	0.1
Released Cadmium (mg/L)	ND	ND	0.01	0.01
Released Barium (mg/L)	ND	ND	0.1	1
Volume of 4% Acetic acid used (mL)	360	360		
Depth (mm)	73	73		
Diameter (mm)	90	90		
Comment	PASS	PASS		

Sample Description:

- 1. Glazed cream ceramic cup w/ dark green pattern
- 2. Glazed dark blue ceramic cup w/ cream pattern



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Conditions/Terms-and-Comment-Service-Propositions-Propositions-Propositions-Propositions-Propositions-Propositions-India

Attention: 10 creck the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 4443, or email: CN. Doccheck@egs.com
Room (101-001, Plant 4 & Room 101, Plant 2 & Room 101, Plant 3 & Room 301-501, Plant 3, Eanglas (Banical) Industrial Plant Area, No.00, Jihua Rood, Banica Community, Banica Street, Longgang District, Stenzhen, Guangdong China 510129 www.sgsgroup.com.cn
中国・广东・深圳市龙岗区坂田街道坂田社区吉华路 430 号江源(坂田)工业厂区厂房 4 号 101-901、2 号 101、3 号 101、3 号 301-501 邮第: 518129 t (86-755) 253288888 sgs.china@sgs.com



Test Report No.: T52510330555TC Date: AUG 15, 2025 Page 7 of 8

Toot Itom	Results		Reporting	Drinking
Test Item	1	2	Limit	Rim Limit
Released Lead (mg/dm²)	ND	ND	0.01	0.02
Released Cadmium (mg/dm²)	ND	ND	0.001	0.002
Released Barium (mg/dm²)	ND	ND	0.1	0.2
Volume of 4% Acetic acid used (mL)	150	150		
Surface Area (dm²)	1.13	1.13		
Depth (mm)	73	73		
Diameter (mm)	90	90		
Comment	PASS	PASS		

Sample Description:

- 1. Glazed cream ceramic cup w/ dark green pattern
- 2. Glazed dark blue ceramic cup w/ cream pattern

Note: 1. mg/L = milligram per liter

2. mg/dm² = milligram per square decimeter

3. ND = Not Detected

Remark:

- 1. Flatware Articles with an internal depth not exceeding 25 mm and articles which cannot be filled.
- 2. Hollow-ware Articles which can be filled.
- 3. Drinking rim –The drinking rim is the 20mm wide section, measured downwards from the upper edge along the wall of the vessel, of the external surface of a drinking vessel.

Remark:

- 1. Since the data and / or information above division line of front page is provided by the applicant, the relevant results or conclusions of this report are only made for these data and / or information, SGS shall not be responsible for the authenticity and integrity of such data and information and the validity of the results and / or conclusions arising therefrom. Testing results only apply to the sample as received.
- 2. Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (*w*=0) stated in ILAC-G8:09/2019.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Conditions/Terms-and-Comment-Service-Proposed-Propos

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 8307
1443, or email: CN.Doccheck@egs.com
Rom IIIV4M; Ran 14 8 Rom III, Plant 13 Rom 101, Plant 13 Rom 10



Test Report No.: T52510330555TC Date: AUG 15, 2025 Page 8 of 8

Sample Picture (As received)

Pic.1



SGS authenticate the photo on original report only

*** End of Report ***



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Conditions/Terms-and-Conditions/Terms-and-Conditions/Terms-and-Compant-Service-Terms-En/Conditions-E

1443, or email: CN. Doccheck@sgs.com Room 11/901, Part A Room 11/Part 2 A Room 11/Part 2