Annual Test Data



Ford Specification: WSS-M11P62 Rev: June 2007 Lab: 3M Lab Product: 9456 Lot#: 87785 Substrate: ABS; Product: 9456 Lot#: 87785 Substrate: Aluminum Foil

<u>TEST</u> Flammability*	TEST METHODS SAE J369	SPECIFICATION 100 mm/min max	<u>RESULT</u> SE**
Fog Test*** 1 hr 16 hr	SAE J1756****	70 min 70 min no oily deposits no crystals no film	84.2 96.3 Pass Pass Pass
Odor dry wet	SAE J1351	2 rating max 2 rating max	1 2

* - Samples were created with the adhesive applied to a 2 mil aluminum foil to support during test.

** - Self Extinguishing

*** - Samples were bonded between ABS and 2 mil aluminum foil and results were taken from the ABS side of the panel.
**** - For section 5.2 of SAEJ1756 the dishwasher has been replaced with handwashing using Alconox (tm). Test

**** - For section 5.2 of SAEJ1756 the dishwasher has been replaced with handwashing using Alconox (tm). Test washing with the closest equivalent dishwasher left water spots on the glassware. Handwashing has produced clean glassware. At this time the difference in results cannot justify the purchase of a dedicated washing unit.

Data Test Date: 10/31/2014

Approved by IATD Quality:

Huv Ho

Test Coordinator Fax: (651) 737-5477

Office: (651)737-6071

Important notice to purchaser All statements, technical information and recommendations herein are based on tests we believe to be reliable, but the accuracy of completeness thereof is not guaranteed, and the following is made in lieu of all warranties, expressed or implied, including the implied warranties of merchantability and fitness for purpose: Seller's and manufacturer's only obligation shall be to replace such quantity of product to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith. Neither seller nor manufacturers shall be liable either in tort or in contract for any loss or damage, direct, incidental, or consequential, arising out of the use of or the inability to use the product. No statement or recommendation not contained herein shall have any force or effect unless in agreement signed by officers of seller or manufacturers.