

FREE-SAT® FS-ULT70

PRESATURATED POLYESTER WIPES, SEALED-EDGES




Technical Data Sheet

Description

FREE-SAT® ULTIMATE 70™ cleanroom wipes are made from double knit 100% polyester with laser cut sealed edges and presaturated with isopropyl alcohol. These wipes are manufactured in a cleanroom environment and cleanroom packaged.

Features & Benefits

- Wiping and cleaning all aspects of cleanroom
- ISO Class 3-8 Cleanrooms
- Removal of solutions such as disinfectants, adhesives, residues, etc.



Performance Characteristics:

Test	Value
Basis Weight (g/m ²)	140 gsm
Thickness	0.48 mm
Absorbency Rate & Capacity	
Absorbency Capacity (IEST-RP-CC004.3, Sec 8.1)	310 mL / m ²
Absorbency Rate (IEST-RP-CC004.3, Sec 8.2)	1 sec
Non-volatile Residue, NVR (IEST-RP-CC004.3, Sec 7.1.2)	
DI water extractant	0.14 mg/g
IPA extractant	0.52 mg/g
Releasable Particles	
LPC ≥ 0.5 µm (IEST-RP-CC004.3, Sec 6.1.4)	7.0 x 10 ⁶ counts/m ²
Ions (IEST-RP-CC004.3, Sec 7.2.2)	
Chloride (Cl)	0.000174 mg/g
Nitrates (NO ³)	0.000019 mg/g
Nitrite (NO ²)	0.000025 mg/g
Sulphate (SO ⁴)	0.000083 mg/g
Sodium (Na)	0.000312 mg/g
Potassium (K)	0.000227 mg/g
Magnesium (Mg)	0.000049 mg/g
Calcium (Ca)	0.000021 mg/g
Organics by FTIR (IEST-RP-CC004.3, Sec 7.2.1)	No Silicone oil, Amide, DOP detected

Packaging:

ITEM	Description	Size	Wipes/Unit	Units/Case
FS-ULT70-99.30	Presaturated with 70% IPA/30% DI Water	9" x 9"	30	12
FS-ULT70-99.40	Presaturated with 70% IPA/30% DI Water	9" x 9"	40	12
FS-ULT70-99.99	Presaturated with 99% IPA/1% DI Water	9" x 9"	30	12
FS-ULT70-99CB	Validated Sterile, Presaturated with 70% IPA/30% DI Water	9" x 9"	30	10

The above is typical physical property test data applicable to the sample reference name and should not be construed as a specification.

Disclaimer: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the material are responsible for assuring that it is suitable for their needs, environment and end use. All data is subject to change as High-Tech Conversions deems appropriate.

