

# 3M

## Scotch-Weld™

### Epoxy Adhesive

#### 2158 B/A

**Technical Data**

**December, 2009**

#### Product Description

3M™ Scotch-Weld™ Epoxy Adhesive 2158 B/A is a gray, two-part, high strength adhesive that chemically cures at room temperature. It has good adhesion to a variety of substrates including metals, many plastics, wood and concrete.

#### Features

- Equal mix ratio by weight or volume.
- Good adhesion to damp concrete.

#### Typical Uncured Properties

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

	<b>Base</b>	<b>Accelerator</b>
<b>Physical</b>		
<b>Color:</b>	White	Dark Gray
<b>Base:</b>	Modified Epoxy	Synthetic Resin
<b>Net Weight: (lbs./gal.)</b>	13.0 ± .2	12.8 ± .4
<b>Viscosity: (Approx. cps @ 75°F [24°C])</b>	Brookfield RVF #7 sp. @ rpm 250,000-450,000 cps	Brookfield RVF #7 sp. @ rpm 200,000-800,000 cps
<b>Mix Ratio: by Weight</b>	1 part	1 part
<b>Mix Ratio: by Volume</b>	1 part	1 part
<b>Work Life: (Approximate time for a 100 gram quantity @ 75°F [24°C])</b>	2 hours	

**3M™ Scotch-Weld™**  
**Epoxy Adhesive**  
 2158 B/A

**Typical Cured Properties**

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

**Physical**

<b>Color</b>	Gray
<b>Shore D Hardness ASTM D-2240</b>	85
<b>Time to Handling Strength at 75°F (24°C)</b>	8-12 hours
<b>Time to Full Cure at 75°F (24°C)</b>	7 days

**Thermal**

<b>Glass Transition Temperature</b>	52°C
<b>Thermal Coefficient of Expansion</b>	53 x 10 <sup>-6</sup> (-50 to +30°C) in./in./°C 135 x 10 <sup>-6</sup> (+70 to +130°C) in./in./°C
<b>Thermal Conductivity</b>	.283 BTU/Hr/Ft <sup>2</sup> /°F/Ft

**Electrical**

<b>Dielectric Constant (1 khz @ 23°C)</b>	5.6
<b>Dissipation Factor (1 khz @ 23°C)</b>	0.019
<b>Dielectric Strength</b>	980 volts/mil
<b>Volume Resistivity</b>	1.4 x 10 <sup>15</sup> ohm-cm

# 3M™ Scotch-Weld™ Epoxy Adhesive 2158 B/A

---

## Handling/Curing Information

## Directions For Use

1. For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. The amount of surface preparation depends on the required bond strength and the environmental aging resistance desired by user. For specific surface preparations on common substrates, see the section on surface preparation.
2. Use gloves to minimize skin contact with adhesive.
3. This product consists of two parts. Mix thoroughly by weight or volume in the proportions specified in the Uncured Properties Section. Mix approximately 15 seconds after a uniform color is obtained.
4. For maximum bond strength apply product evenly to both surfaces to be joined.
5. Application to the substrates should be made within 120 minutes. Larger quantities and/or higher temperatures will reduce this working time.
6. Join the adhesive coated surfaces and allow to cure at 60°F (16°C) or above until firm. Heat, up to 200°F (93°C), will speed curing.
7. The following times and temperatures will result in a full cure:

<u>Cure Temperature</u>	<u>Time</u>
75°F (24°C)	7 days
150°F (49°C)	120 minutes
200°F (93°C)	30 minutes

8. Keep parts from moving until handling strength is reached. Contact pressure is necessary. Maximum shear strength is obtained with a 3-5 mil bond line.
9. Excess uncured adhesive can be cleaned up with ketone type solvents.\*

Adhesive coverage: A 0.005 in. thick bond line will yield a coverage of 320 sq. ft./gallon.

**\*Note:** When using solvents, extinguish all ignition sources, including pilot lights, and follow manufacturer's precautions and directions for use.

---

## Application and Equipment Suggestions

These products may be applied by spatula, trowel or flow equipment.

Two-part mixing/proportioning/dispensing equipment is available for intermittent or production line use. These systems are ideal because of their variable shot size and flow rate characteristics and are adaptable to most applications. For more information, contact your local 3M sales representative.

# 3M™ Scotch-Weld™ Epoxy Adhesive 2158 B/A

---

## Surface Preparation

For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. The amount of surface preparation depends on the required bond strength and the environmental aging resistance desired by user.

The following cleaning methods are suggested for these common surfaces:

### Steel:

1. Wipe free of dust with oil-free solvent such as acetone, isopropyl or alcohol solvents.\*
2. Sandblast or abrade using clean fine grit abrasives.
3. Wipe again with solvent to remove loose particles.
4. If a primer is used, it should be applied within 4 hours after surface preparation.

### Aluminum:

1. Vapor Degrease: Perchloroethylene condensing vapors for 5-10 minutes.\*
2. Alkaline Degrease: Oakite 164 solution (9-11 oz./gallon water) at 190°F ± 10°F (88°C ± 5°C) for 10-20 minutes. Rinse immediately in large quantities of cold running water.
3. Acid Etch: Place panels in the following solution for 10 minutes at 150°F ± 5°F (66°C ± 2°C).

Sodium Dichromate	4.1-4.9 oz./gallon
Sulfuric Acid, 66°Be	38.5-41.5 oz./gallon
2024-T3 aluminum (dissolved)	0.2 oz./gallon minimum
Tap Water as needed to balance	

**Note:** Read and follow component supplier's environmental health and safety recommendations prior to preparation of this etch solution.

4. Rinse: Rinse panels in clear running tap water.
5. Dry: Air dry 15 minutes; force dry 10 minutes at 150°F ± 10°F (66°C ± 5°C).
6. If primer is to be used, it should be applied within 4 hours after surface preparation.

### Plastics/Rubbers:

1. Wipe with isopropyl alcohol.\*
2. Abrade using fine grit abrasives.
3. Wipe with isopropyl alcohol.\*

### Glass:

1. Solvent wipe surface using acetone or methyl ethyl ketone (MEK).\*
2. Apply a thin coating (0.0001 in. or less) or primer such as 3M™ Scotch-Weld™ Structural Adhesive Primer EC-3901 to the glass surfaces to be bonded and allow the primer to dry before bonding.

**\*Note:** When using solvents, extinguish all ignition sources, including pilot lights, and follow manufacturer's precautions and directions for use.

**3M™ Scotch-Weld™**  
**Epoxy Adhesive**  
 2158 B/A

**Typical Adhesive  
 Performance  
 Characteristics**

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

**1. Overlap Shear Strength (psi) ASTM D-1002-72**

<u>Test Temp</u>	<u>Aluminum FPL Etch</u>
-67°F (-55°C)	1500
75°F (24°C)	2000
180°F (82°C)	400

**2. T-Peel Strength (piw) ASTM D-1876-61T**

<u>Test Temp</u>	<u>Aluminum FPL Etch</u>
75°F (24°C)	3

**3. Environmental Aging**

Overlap Shear Strength (psi) after Environmental Aging Aluminum to Aluminum (ASTM D-1002-72).

Tap Water	30 days	2800
Air @ 300°F (149°C)	30 days	2600
Salt Spray (20% @ 95°F [35°C])	30 days	1500
Relative Humidity (100% @ 120°F [49°C])	30 days	2500

**Note:** All data developed using a 7 day @ 75°F (24°C), 2 psi cure.

# 3M™ Scotch-Weld™ Epoxy Adhesive 2158 B/A

---

**Storage** Store product at 60-80°F (15-27°C) for maximum storage life.

---

**Shelf Life** 3M™ Scotch-Weld™ Epoxy Adhesive 2158 B/A has a storage life of two years in unopened containers. Rotate stock on a “first in-first out” basis.

---

**Precautionary Information** Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

---

**Technical Information** The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

---

**Product Use** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

---

**Warranty, Limited Remedy, and Disclaimer** Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

---

**Limitation of Liability** Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

**ISO 9001:2000**

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.



## Industrial Adhesives and Tapes Division

3M Center, Building 225-3S-06  
St. Paul, MN 55144-1000  
800-362-3550 • 877-369-2923 (Fax)  
www.3M.com/industrial



*Recycled Paper*  
40% pre-consumer  
10% post-consumer

3M and Scotch-Weld are trademarks of 3M Company.  
Printed in U.S.A.  
©3M 2009 78-6900-9910-2 (12/09)