



Equalizer, an ultra high solids finish only requires 3 coats for maximum shine. Patented polymers make for a next generation formula. Equalizer will significantly lower the cost of clean by providing far less labor to the stripping and reapplication process than was ever thought possible. No seal is necessary unless the floor is extremely porous. Equalizer has excellent dirt resistance. It provides resistance to black marks, scuffs, scratches, and heel marks. Little to no buffing is required. Once floors are coated with Equalizer, daily/weekly maintenance is much easier. Just damp mop or auto scrub the floor using Hillyard Super Shine All® or Top Clean®. Equalizer will respond brilliantly to occasional burnishing. Equalizer is tough and retains its shine longer. With improved shine and depth of gloss Equalizer will reduce in floor care costs. A cleaner looking floor over time means lower total cost to you and higher satisfaction with the appearance of the floor. Only one coat is necessary for a scrub and recoat. Equalizer seals and finishes in one operation. No need for a sealer. Although high solid finishes are typically harder to apply Equalizer goes down smooth with a flat mop applicator. Strip floors first, then apply coats with a flat mop applicator allowing 45 to 55 minutes between coats. Equalizer is conveniently packaged in one, five and 55 gallon containers and meets slip resistance using ASTM D2047 and Underwriters Laboratories, Inc's. Method 410. Ask your Hillyard sales consultant about the benefits of coating your floors with Equalizer and how it can give you easy-to-maintain, safer floors. Just another example of high quality from Hillyard.

### Features & Benefits

Ultra High Solids 30%

2 coats equals 4 coats of other finishes which reduces labor and downtime.

Tough polymer system extends shine and gloss.

### Item Number & Unit of Measure

Item Number	HIL0055309
Unit of Measure	55 gal Drum

### Specifications

Color	White
Appearance	Milky Emulsion
Fragrance	Non-Objectionable
Formula Type	Liquid
Dilution Ratio	RTU
PH	8.00 - 9.00
Non-Volatile Matter	29.50 - 30.50%
Solids Content	30
Coverage SqFt/Gallon	1500-2000
Dry Time (hrs.)	1
Sheen	Gloss

### Safety

See safety datasheet (if applicable) and product label for safety information, handling and proper use.

### Directions for Use

**Preparation: New floors:** After resilient flooring has been installed and the adhesive has cured for at least 2 weeks, scrub with a solution of Hillyard Recoat Prep or Assurance®, following label directions, and a blue pad to remove factory finish. Pick up scrubbing solution with an automatic scrubber or wet vacuum. Flood rinse with a solution of Hillyard Nutra-Rinse® and pick up solution with an automatic scrubber or wet vacuum. Damp mop rinse twice with water and allow to dry for at least 1 hour. **Scrub and recoat:** Scrub the existing floor polish with a solution of Hillyard Recoat Prep or Assurance, following label directions, and a blue pad. Pick up scrubbing solution with an automatic scrubber or wet vacuum. Flood rinse with a solution of Hillyard

# Equalizer® Floor Finish (continued)



Nutra-Rinse and pick up solution with an automatic scrubber or wet vacuum. Damp mop rinse twice with water and allow to dry for at least 1 hour.

**Stripping:** Strip Equalizer or other polishes from the floor with a solution of Hillyard Arsenal® Stripper, Devastator®, or Power-Strip®, following label directions. Pick up scrubbing solution with an automatic scrubber or wet vacuum. Flood rinse with a solution of Hillyard Nutra-Rinse and pick up solution with an automatic scrubber or wet vacuum. Damp mop rinse twice with water and allow to dry for at least 1 hour.**Application:** When using a sealer, apply a minimum of 2 coats of Equalizer at a rate of 1500-2000 ft<sup>2</sup>/gallon with a microfiber flat finish mop or Multi-Flo® XP. Allow each coat to dry a minimum of 45 minutes to 1 hour before applying the next. When a sealer is not used, apply a minimum of 3 coats of Equalizer.**NOTE:** Allow for longer dry time between coats of finish if the humidity is above 80% or the floor temperature is below 60°F (16°C). For best results, do not apply more than 3 coats per day.**Maintenance:** Use a cotton dust mop, treated with Hillyard Super Hil-Tone®, daily to remove loose dirt and grit. Damp mop or autoscrub, as scheduled, with Hillyard Super Shine-All®, Top Clean®, or Arsenal® Heavy Duty Floor Cleaner. After the floor has been cleaned, gloss may be restored by spray buffing with Hillyard Hil-Glo®, according to label directions. Scrub and recoat, as scheduled, with 1 coat of Equalizer.

**FLOOR PAD RECOMMENDATIONS: Stripping:** black; **Scrub and Recoat:** blue; **Autoscrubbing:** red.

**NOTICE:** Do not use an ammoniated cleaner for daily care. If the floor is very porous, seal with Hillyard Hil-Tex+®, Seal 341®, or Seal 340® before applying Equalizer. If stains are a problem, seal with Strong Guard®. Keep container closed when not in use. Do not pour unused finish or seal back into the original container.

(UL LOGO) FLOOR COATING AND FINISHING MATERIAL AS TO SLIP RESISTANCE ONLY. 186S

-

Equalizer meets the CARB VOC requirements

**PROTECT FROM FREEZINGDISCLAIMER OF WARRANTY:** Seller makes no warranty of any kind, express or implied, except that this product shall be of seller's standard quality.