



| | |
|----------------------|-----------|
| Coverage SqFt/Gallon | 1500-2000 |
| Burnishable | Yes |
| Dry Time (hrs.) | 1 |
| Sheen | Gloss |
| UL Certified | Yes |

Safety

See safety datasheet (if applicable) and product label for safety information, handling and proper use.

Directions for Use

Preparation: New floors: After resilient flooring has been installed and the adhesive has cured for at least 2 weeks, scrub with a solution of Hillyard Recoat Prep or Assurance, following label directions, and a blue pad to remove factory finish. Pick up scrubbing solution with an automatic scrubber or wet vacuum. Flood rinse with a solution of Hillyard Nutra-Rinse and pick up solution with an automatic scrubber or wet vacuum. Damp mop rinse twice with water and allow to dry for at least 1 hour. **Scrub and recoat:** Scrub the existing floor polish with a solution of Hillyard Recoat Prep or Assurance, following label directions, and a blue pad. Pick up scrubbing solution with an automatic scrubber or wet vacuum. Flood rinse with a solution of Hillyard Nutra-Rinse and pick up solution with an automatic scrubber or wet vacuum. Damp mop rinse twice with water and allow to dry for at least 1 hour. **Stripping:** Strip North Star or other polishes from the floor with a solution of Hillyard Arsenal Stripper, Devastator, or Power-Strip, following label directions. Pick up scrubbing solution with an automatic scrubber or wet vacuum. Flood rinse with a solution of Hillyard Nutra-Rinse and pick up solution with an automatic scrubber or wet vacuum. Damp mop rinse twice with water and allow to dry for at least 1 hour. **Application:** When using a sealer, apply a minimum of 4 coats of North Star at a rate of 1500-2000 ft²/gallon with a microfiber flat finish mop or Multi-Flo XP. Allow each coat to dry a minimum of 45 minutes to 1

Formulated with durability in mind. It stands up to heavy traffic, dirt, scuffs, and black heel marks. It was built to take advantage of the heat and friction generated by repeated burnishing with ultra-high speed equipment. Burnishing only makes it look better. North Star's advance durability also helps it stand up to repeated scrubbing with water and detergents better than ordinary polishes.

Features & Benefits

A 22% solids formula that requires less coats and less labor

Self-leveling for easy application

A durable coating that buffs back

Item Number & Unit of Measure

| | |
|-----------------|-------------|
| Item Number | HIL0052809 |
| Unit of Measure | 55 gal Drum |

Specifications

| | |
|---------------------|-------------------|
| Color | White |
| Appearance | Milky Emulsion |
| Fragrance | Non-Objectionable |
| Formula Type | Liquid |
| Dilution Ratio | RTU |
| PH | 8.00 - 9.00 |
| Non-Volatile Matter | 22.0% |
| Solids Content | 22.0% |

hour before applying the next. When a sealer is not used, apply a minimum of 6 coats of North Star.

NOTE: Allow for longer dry time between coats of finish if the humidity is above 80% or the floor temperature is below 60°F (16°C). For best results, do not apply more than 3-4 coats per

day. **Maintenance:** Use a cotton dust mop, treated with Hillyard Super Hil-Tone, daily to remove loose dirt and grit. Damp mop or autoscrub, as scheduled, with Hillyard Super Shine-All®, Top Clean®, or Arsenal® Heavy Duty Floor Cleaner. After the floor has been cleaned, gloss may be restored by dry burnishing. Use Hillyard Restorer, as scheduled, to repair and increase the gloss of the finish. Scrub and recoat, as scheduled, with a minimum of 2 coats of North Star. **FLOOR**

PAD RECOMMENDATIONS: Stripping: black; **Scrub and Recoat:** blue; **Autoscrubbing:** red.

NOTICE: Do not use an ammoniated cleaner for daily care. If the floor is very porous, seal with Hillyard Hil-Tex+®, Seal 341® or Seal 340® before applying North Star. If stains are a problem, seal with Strong Guard®. Do not pour unused finish or seal back into the original container.