



# Bona SuperCourt OPTUM®

One-component Waterborne Wood Floor Finish

The leading one-component athletic wood floor finish for durability and appearance



Bona SuperCourt OPTUM® is a premium one-component waterborne athletic wood floor finish. Unsurpassed scuff, scratch and chemical resistance at full cure, exceptional build with excellent flow and leveling.

- Green Seal™ GS-11 Certified
- 24-hours to play!
- MFMA approved
- GREENGUARD Gold certified for indoor air quality
- Very low VOC and low odor
- Clear and colorless, highlighting the true color of stained or natural wood floors
- Will not change color over time, allowing for easy touch-up
- Fast drying – approximately 2-3 hours
- Nonflammable
- Water clean-up



# Bona SuperCourt OPTUM<sup>®</sup>

One-component Waterborne Wood Floor Finish

The leading one-component athletic wood floor finish for durability and appearance

## PHYSICAL CHARACTERISTICS

**Ingredients** - Water, Polymeric resin, N-Methyl-2-Pyrrolidone, Dipropylene Glycol Monomethyl Ether and Dipropylene Glycol n-Butyl Ether

**Color** – Milky, off white (wet)

**pH** – 8.3

**Solids** – 30%

**Viscosity** – (#4 Ford cup @ 25 ° C) approx. 16 seconds

**Density** – 8.52 lbs./gallon (1.02 S.G.)

**US Regulatory VOC Compliant** – 275 g/L

**Gloss Level** – (60°) 88+

**Odor** – Non-offending

**Stability** – 1-year shelf life in unopened container

**Packaging** – 5-gallon plastic pail – Comes complete with crosslinker

## APPLICATION CHARACTERISTICS

**Clarity** – Clear when dry

**Leveling** – Excellent

**Defoaming** – Excellent

**Drying Time** – 2-3 hours

**Application Tools** – Bona<sup>®</sup> Swivel Head Floor Coater, Bona<sup>®</sup> Swedish Roller

**Coverage** – 500-600 square feet per gallon

**Ready to Play** – 24 hours

**Maximum Cure** – one week

## RECOMMENDED USE

Basketball courts, multi-purpose gym, stage, aerobic, dance and yoga floors, volleyball courts, racquetball, squash, and badminton.

**BEFORE USING, READ ALL DIRECTIONS AND SAFETY DATA SHEETS.**

FOR TECHNICAL ADVICE: Call Bona US at 800-872-5515

## RESPONSE

In case of eye contact, flush immediately with water. Get medical attention if irritation occurs. For skin, wash thoroughly with soap and water. If affected by inhalation, remove to fresh air. If swallowed, drink 1 or 2 glasses of water to dilute. Do not induce vomiting. Get medical attention if symptoms occur.

## COMPATIBILITY

Bona SuperCourt OPTUM will adhere to most stains, paints, sealers and finishes after proper preparation and dry times. Do not apply Bona SuperCourt OPTUM to raw wood, or wood flooring in which the surface temperature is below 50°F (10°C). Stain, sealer, paint, and finish results may vary widely depending on the wood species, especially on oily and resinous types. ALWAYS PREPARE A SAMPLE OR TEST AREA TO DETERMINE COMPATIBILITY, APPEARANCE AND DESIRED RESULTS.

## FOR BEST RESULTS

Bona SuperCourt Cleaner Concentrate, an auto scrubber with Bona SuperCourt Athletic Floor Care (AFC) Microfiber Scrubbing Pads, Bona SuperCourt Athletic Floor Care Mop System, Bona FlexiSand DCS<sup>®</sup> Buffer, Bona Multidisc drive plate, 180-grit Bona Diamond abrasives, Bona DCS Back Vac, Bona 18" Swivel Head Floor Coater and 18" Bona Floor Coater Sleeve, Bona SuperCourt OPTUM finish, a dispensing can, and blue tape.

## RECOATING

**1. Evaluate the Floor** – Evaluate the entire wood floor for scuff marks, current finish condition/peeling, cupping and other damage, and overall floor appearance. **2. Prepare the floor** – gather all recommended tools and materials for the job. Secure the work area and post signs on entrance doors with "Do Not Enter." Use the Bona SuperCourt Microfiber Dusting Pad to dry dust the floor. Remove tape/sticky



# Bona SuperCourt OPTUM®

One-component Waterborne Wood Floor Finish

**The leading one-component athletic wood floor finish for durability and appearance**

spots from the floor by cleaning with auto scrubber SuperCourt AFC Microfiber Scrubbing Pads and Bona SuperCourt Cleaner Concentrate. Let dry. **3. Abrasion** – Once the floor has dried, abrade the floor using the Bona FlexiSand DCS Buffer and DCS Back Vac with 180-grit Bona Diamond abrasives on a Bona Multidisc. Abrade the entire work area. Work in sections, making sure to overlap sections. (Bona Diamond abrasives will last 4000-6000 square feet before replacement.) **4. Post-Abrasion Cleaning** – Vacuum and dry tack the entire floor to remove abrasive dust. Auto scrub or wet tack entire floor. **5. Coating Preparation** – before coating, tape-off floor plates, outlets, or areas needing protection from the floor finish. Strain finish and pour into clean dispensing containers or work from pail. Clean and rinse applicators. Place finish every 2500 square feet to assist with coverage rate. Have an exit strategy. For more information, and to watch a video on the Recoat Process: visit [www.bona.com](http://www.bona.com).

## RECOMMENDED APPLICATORS

18" Bona Swivel Head Floor Coater with a Bona Floor Coater Sleeve.

## NOTE

Use a clean applicator for the sealer and a separate clean applicator for finish.

## MIXING INSTRUCTIONS

Remove lid and stir thoroughly before use.

## FINISHING

1. Pour a 4"-6" wide line of finish along the starting wall. Go with the grain of the wood. 2. Using a clean, pre-dampened applicator; draw the applicator forward, with the grain of the wood, moving the finish toward the opposite wall. Holding the applicator at a "snowplow" angle will help maintain a wet edge at all times. 3. At

the end of each run, turn the applicator and pull it toward you through the puddle and pad out the applicator parallel to the wet edge. 4. Feather out all turns. Do not push too hard or too fast to avoid dripping or splattering. 5. Missed areas can be touched up if seen right away. 6. BE SURE YOU ARE USING THE RECOMMENDED COVERAGE OF 500-600 SQUARE FEET PER GALLON. DO NOT SPREAD TOO THIN. 7. Allow the first coat to dry 2-3 hours. High humidity and/or low temperature conditions will extend the dry time (recommended conditions of 65-80°F/40-60% relative humidity). 8. Allow final coat to dry at least 24 hours before use.

## INTERCOAT ABRASION

It is not necessary to abrade between coats of Bona SuperCourt OPTUM unless more than 48 hours has passed since the previous coat was applied. For smoothest results, abrade between all coats as necessary with Bona Conditioning Pads or a Bona Multidisc and 240-grit Bona Diamond abrasives.

## CURING

The curing process takes approximately 7 days. Do not replace area rugs until the floor has fully cured. The floor may be played on after 24 hours but remains susceptible to scuffing or marring until completely cured. No wet cleaning during the first week, only dry dust with a Bona SuperCourt Microfiber Dusting Pad. (Do not use dry dust mop treatment chemicals on wooden floors.)

## CLEAN-UP

Application tools should be cleaned with water and stored in an airtight container. Recycle container when empty.



# Bona SuperCourt OPTUM®

One-component Waterborne Wood Floor Finish

The leading one-component athletic wood floor finish for durability and appearance

## STORAGE

Nonflammable - Bona SuperCourt OPTUM should be stored in a climate-controlled environment. KEEP FROM FREEZING. Do not store above 100° F (38° C).

## MAINTENANCE

Place walk-off mats at all entrance doorways to keep out excessive dirt and grit. For best results, see Bona SuperCourt Athletic Floor Care System products for optimal wood floor care.

## ORDERING INFORMATION

Item #	Description	Size	No. Case	Weight/ Lbs.
WT763055001	Bona SuperCourt OPTUM	5 Gallon	1	46.15