



Annual Test Data

Ford

Specification: WSS-M11P62 Rev: June 2007 Lab: 3M Lab
Product: 9472 950 9672 969 Lot#: 613733 Substrate: ABS;
Product: 9472 950 9672 969 Lot#: 613733 Substrate:
Aluminum Foil

<u>TEST</u>	<u>TEST METHODS</u>	<u>SPECIFICATION</u>	<u>RESULT</u>
Flammability*	SAE J369	100 mm/min max	SE**
Fog Test***	SAE J1756****		
1 hr		70 min	92.1
16 hr		70 min	95.7
		no oily deposits	Pass
		no crystals	Pass
		no film	Pass
Odor	SAE J1351		
dry		2 rating max	1
wet		2 rating max	2

* - Samples were created with the adhesive applied to a 2 mil aluminum foil to support during test.

** - Self Extinguishing

*** - Samples were bonded between ABS and 2 mil aluminum foil and results were taken from the ABS side of the panel.

**** - For section 5.2 of SAEJ1756 the dishwasher has been replaced with handwashing using Alconox (tm). Test washing with the closest equivalent dishwasher left water spots on the glassware. Handwashing has produced clean glassware. At this time the difference in results cannot justify the purchase of a dedicated washing unit.

Data Test Date: 01/31/2015

Approved by IATD Quality:

Huy Ho
Test Coordinator
Office: (651)737-6071
Fax: (651) 737-5477

Important notice to purchaser All statements, technical information and recommendations herein are based on tests we believe to be reliable, but the accuracy of completeness thereof is not guaranteed, and the following is made in lieu of all warranties, expressed or implied, including the implied warranties of merchantability and fitness for purpose: Seller's and manufacturer's only obligation shall be to replace such quantity of product to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith. Neither seller nor manufacturers shall be liable either in tort or in contract for any loss or damage, direct, incidental, or consequential, arising out of the use of or the inability to use the product. No statement or recommendation not contained herein shall have any force or effect unless in agreement signed by officers of seller or manufacturers.