



CRC Industries NZ, Auckland NZ

**I. Product Description**

ADOS Roof & Gutter Silicone is a single component, fast curing, room temperature vulcanising silicone.

**II. Application and Directions****Preparation:**

- All surfaces must be clean, dry, sound and free from dust, oil and any other contamination.
- Metals should be cleaned with a solvent soaked clean cloth. Solvent should then be wiped from the surface with a clean, dry cloth.
- Use alcohol on glass and for plastic, consult the supplier for recommended cleaning solvent.

**Application:**

- Cut nozzle to a sharp angle, slightly wider than desired bead.
- Extrude sealant with a gun and tool immediately (within 5 minutes) with a round spatula to spread the sealant against the backup material and the joint surfaces.
- When necessary to obtain a good appearance, masking tape is recommended. This should be removed immediately after tooling before a skin forms.
- Immediately after completion, clean excess sealant off surfaces, tools and hands with a clean, dry cloth.

**Clean Up:**

- Use ADOS Solvent N to clean uncured product off equipment and surfaces. Can also help to soften cured product.

**Note:** Not recommended for use on submerged joints, especially where porous substrates permit water to the bond interface. Not suitable for use on polycarbonate.

**Estimating Requirements – linear metres per cartridge for various joint dimensions:**

Depth mm	Width mm						
	3.3	6.4	9.7	12.7	16.0	19.2	25.4
3.3	29.7	14.88	9.93	7.44	5.94	4.97	3.72
4.9		9.93	6.64	4.97	3.96	3.31	2.48
6.4		7.42	4.97	3.72	2.97	2.49	1.86
9.7			3.31	2.48	1.98	1.64	1.23

**III. Features & Benefits**

- Fast curing
- Will not harm galvanised iron
- Specifically for work on roofs and gutters
- Neutral cure



CRC Industries NZ, Auckland NZ

#### IV. Typical Properties and Characteristics

##### Physical Properties & Performance Characteristics:

Composition	Silicone polymer
Curing Method	Neutral (Oxime)
Colour	Translucent
Service Temperatures	-60 °C to +150 °C
Peel Strength (ASTM C794)	2.9 kN/m
Hardness (Shore A)	20-35
Slump (w = 20mm)	< 1mm
Tensile Strength	≥ 1.0MPa
Dynamic Joint Movement	± 20%
Density	1.04
Tooling Time	6-20 minutes
Toxicity	Not suitable for fish tanks
Tack Free Time	20 minutes
Cure Time (5mm, 20 °C / 53% RH)	2 days

#### V. Package Description

Part Number	Size
8315	310ml Cartridge

#### VI. Special Precautions

##### General:

Keep locked up. Store in cool, dry, protected area. Use with adequate ventilation. Do not eat, drink or smoke while using. Dispose of empty containers safely. All unused product should be disposed of in conformance with local and HSNO regulations, do not contaminate water supply.

##### First Aid:

Swallowed – Do not induce vomiting. Give water to rinse out mouth, then provide liquid slowly and as much as casualty can comfortably drink. Seek medical advice.

Skin – Immediately flush body and clothes with large amounts of water, using safety shower if available. Quickly remove all contaminated clothing, including footwear. Transport to hospital or doctor.

Eyes – Hold open and flush eye continuously with running water. Continue flushing until advised to stop by the Poisons Information Centre or a doctor, or for at least 15 minutes. Transport to hospital or doctor without delay.

Inhalation – Remove from contaminated area. Lay patient down. Keep warm and rested. Transport to hospital or doctor.

Refer to Material Safety Data Sheet for more details.

TECHNICAL DATA SHEET Version 09/2012

**PRODUCT WARRANTY:** CRC offers a conditional warranty of this product for the period of 2 years from the date of manufacture.

**DISCLAIMER:** All information on this data sheet is based on testing by CRC Industries NZ. All products should be tested for suitability on a particular application prior to actual use. CRC Industries makes no representations or warranties of any kind concerning this data.