

**Test Report** No.T52010291643TC Date: SEP 25, 2020 Page 1 of 5

## BLOOMINGVILLE A/S LENE HAUS VEJ 3-5 DK-7430 IKAST DENMARK

The following samples were submitted and identified by/on behalf of the client as:

TRAY GREY, STONEWARE

Item No. : 82049581 P.O. No. : 65899

Importer : BLOOMINGVILLE A/S
Buyer : BLOOMINGVILLE A/S
Supplier : BLOOMINGVILLE A/S
Manufacturer : BLOOMINGVILLE A/S

Country of Origin : CHINA

Country of Destination : DENMARK

\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*\*

Sample Receiving Date : SEP 21, 2020

Testing Period : SEP 21, 2020 TO SEP 24, 2020





**Test Report** 

No. T52010291643TC

Date: SEP 25, 2020

Page 2 of 5

Test	Conclusion	
1.	The European Council Directive 84/500/EEC and its amendment 2005/31/EC—Ceramic Articles intended to Come into Contact with Foodstuffs - migration Lead and Cadmium	PASS
2.	Danish Ordinance on materials and articles intended for food contact (BEK nr 1248 of 30 October 2018) – Leachable Lead and Cadmium	PASS

\*\*\*\*\*\*\* FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) \*\*\*\*\*\*\*\*

Signed for and on behalf of SGS-CSTC Standards Technical Services Co., Ltd. Shenzhen Branch Testing Center

Qu Ping, Kiky Dept. Manager





**Test Report** No. T52010291643TC Date: SEP 25, 2020 Page 3 of 5

Test Results:

1

1

## 1. European Council Directive 84/500/EEC & its amendment 2005/31/EC - Leachable Lead and Cadmium

Test Method: With reference to European Directive 84/500/EEC and its amendment 2005/31/EC. Analysis

was performed by ICP-OES.

Sample 001 Category 1

Vol. of 4%HAc used	<u>Depth</u>	Surface Area		
<u>(mL)</u>	<u>(mm)</u>	<u>(dm²)</u>		
480	20	3.81		

Leachable Lead Leachable Cadmium

(mg/dm²) (mg/dm²) <0.1 <0.02

Limit 0.8 0.07

Test Part Description:

Specimen No. SGS Sample ID Description

SN1 SZX20-023366.001 Glazed green ceramic irregular plate

Remarks:

(1) mg/dm<sup>2</sup> = milligram per square decimeter

(2) mg/kg = milligram per kilogram

(3) °C= degree Celsius

(4) < = less than

(5) MDL = Method Detection Limit

(6) ND = Not Detected ( < MDL)

#### Notes:

Category 1: Articles that cannot be filled and articles that can be filled, the internal depth of which does not exceed 25 mm.

Category 2: Articles, not in categories 1 or 3, which can be filled.

Category 3: Cooking ware; packaging and storage vessels having a capacity of more than three liters.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printer overleaf, available on request or accessible at http://www.ags.com/en/ferms-and-Conditions.aspx and, for electronic format documents subject to Terms and Conditions for Electronic Documents at http://www.ags.com/en/ferms-and-Conditions/Terms-e-Document.aspx Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits or Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or faisification of the content of appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



**Test Report** 

No. T52010291643TC

Date: SEP 25, 2020

Page 4 of 5

# 2. Danish Ordinance on materials and articles intended for food contact (BEK nr 1248 of 30 October 2018) - Leachable Lead and Cadmium

Method: With reference to Danish Ordinance on materials and articles intended for food contact (BEK nr 1248 of 30 October 2018). Analysis was performed by Atomic Absorption Spectrometry.

Test Item	Glazed green ceramic irregular plate				Reporting	Category 1
rest item	1	2	3	4	Limit	Limit
Released Lead (mg/dm²)	ND	ND	ND	ND	0.1	0.8
Released Cadmium (mg/dm²)	ND	ND	ND	ND	0.01	0.07
Volume of 4% Acetic acid used (mL)	480	480	480	480		
Surface Area (dm <sup>2</sup> )	3.81	3.81	3.81	3.81		
Depth (mm)	20	20	20	20		
Length (mm)	301	301	301	301		
Comment	PASS					

Note: 1. mg/dm<sup>2</sup> = milligram per square decimeter

2. ND = Not Detected

Remark: 1. Category 1 -

a. Articles which cannot be filled.

- b. Articles for filling, whose internal depth measured between the lowest point and the upper edge horizontal level is not more than 25 mm.
- c. Articles intended to drink of (Lip & rim region).
- 2. Category 2 Articles, not in categories 1 or 3, which can be filled.
- 3. Category 3
  - a. Cooking ware
  - b. Packaging and storage vessels having a capacity of more than three litres.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printeoverleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.gapx">http://www.sgs.com/en/Terms-and-Conditions.gapx</a> and, for electronic format documents subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx">http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx</a> attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Cilent's instructions, if any. The Company's sole responsibility is to its Cilent and this document does not exonerate parties to ransaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduce except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or faisification of the content of appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



**Test Report** 

No. T52010291643TC

Date: SEP 25, 2020 Page 5 of 5

Remark 1: Since the data and / or information above division line of front page is provided by the applicant, the relevant results or conclusions of this report are only made for these data and / or information, SGS shall not be responsible for the authenticity and integrity of such data and information and the validity of the results and / or conclusions arising therefrom. Testing results only apply to the sample as received.

Remark 2: The statement of conformity has considered the decision rule based on the Guarded acceptance (8.3.2 of ISO/IEC GUIDE 98-4:2012). When the measured value falls within the guard band, only the test data and measurement uncertainty will be reported. The guard band is equal to the expanded measurement uncertainty with a 95% coverage probability(k=2), k=10, where k=21 is a probability of False Accept and the Probability of False Reject of the decision rule are 2.5%.

For Upper Tolerance Limit (Tu):

Pass - when the measurement result is below Tu-U95

Fail - when the measurement result is above Tu+U95

Inconclusive - when the measurement result is falling in guard band [Tu-U95, Tu+U95]

For Lower Tolerance Limit (T<sub>L</sub>):

Pass - when the measurement result is above TL+U95

Fail - when the measurement result is below T<sub>L</sub>-U<sub>95</sub>

Inconclusive - when the measurement result is falling in guard band [T<sub>L</sub>-U<sub>95</sub>, T<sub>L</sub>+U<sub>95</sub>]

### Sample Photo:



SGS authenticate the photo on original report only

\*\*\* End of Report \*\*\*



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.ags.com/en/ferms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.ags.com/en/ferms-and-Conditions/Terms-e-Document.aspx.Attention">http://www.ags.com/en/ferms-and-Conditions/Terms-e-Document.aspx.Attention</a> is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company, Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: to check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 830 1443, or email: CN. Doccheck@sgs.com

SSS Bldg, No. 4, Jangheo Industrial Park, No. 430, Jihua Read, Bartlan, Lunggang District, Shenzhen, China 518129 t (86-755) 25328888 f (86-755) 83106190 www.sgsgroup.com.cn 中国・深圳・龙岗区坂田吉华路430号江瀬工业园4栋SGS大楼 邮编: 518129 t (86-755) 25328888 f (86-755) 83106190 e e gss.china@sgs.com