



Diversey™

# Bona SuperCourt OPTUM®

Bona SuperCourt OPTUM® is a premium one-component waterborne athletic wood floor finish. With unsurpassed scuff, scratch and chemical resistance at full cure, this finish provides exceptional build with excellent flow and leveling.

## Features & Benefits

- Premium one-component resin technology
- Superior chemical resistance
- Clear and colorless, highlighting the true color of stained or natural wood floors
- 275 g/L VOC
- MFMA Approved, Green Seal & GREENGUARD Gold certified for indoor air quality

## Applications

- Basketball courts
- Volleyball courts
- Racquetball, squash and badminton courts
- Multi-purpose gym, stage, aerobic, dance and yoga floors



**Wood Care by Diversey**  
Powered by Bona



# Bona SuperCourt OPTUM®

## Use instructions

### NOTE:

- Ensure adequate ventilation during application and drying.
- Dispose or recycle excess or unused product in accordance with local, state & federal regulations.

**RECOATING: 1. Evaluate the Floor** – Evaluate the entire wood floor for scuff marks, current finish condition/peeling, cupping and other damage, and overall floor appearance. **2. Prepare the floor** – gather all recommended tools and materials for the job. Secure the work area and post signs on entrance doors with “Do Not Enter.” Use the Bona SuperCourt Microfiber Dusting Pad to dry dust the floor. Remove tape/sticky spots from the floor by cleaning with auto scrubber SuperCourt AFC Microfiber Cleaning Pads and Bona SuperCourt Cleaner Concentrate. Let dry. **3. Abrasion** – Once the floor has dried, abrade the floor using the Bona FlexiSand DCS Buffer and DCS Back Vac with 180-grit Bona Diamond abrasives on a Bona Multidisc. Abrade the entire work area. Work in sections, making sure to overlap sections. (Bona Diamond abrasives will last 4000-6000 square feet before replacement.) **4. Post-Abrasion Cleaning** – Vacuum and dry tack the entire floor to remove abrasive dust. Auto scrub or wet tack entire floor. **5. Coating Preparation** – before coating, tape-off floor plates, outlets, or areas needing protection from the floor finish. Strain finish and pour into clean dispensing containers or work from pail. Clean and rinse applicators. Place finish every 2500 square feet to assist with coverage rate. Have an exit strategy. For more information, and to watch a video on the Recoat Process: visit [www.bona.com](http://www.bona.com).

**RECOMMENDED APPLICATORS:** 18” Bona Swivel Head Floor Coater with a Bona Floor Coater Sleeve. NOTE: Use a clean applicator for the sealer and a separate clean applicator for finish.

**MIXING INSTRUCTIONS:** Remove lid and stir thoroughly before use.

**FINISHING: 1.** Pour a 4”-6” wide line of finish along the starting wall. Go with the grain of the wood. **2.** Using a clean, pre-dampened applicator; draw the applicator forward, with the grain of the wood, moving the finish toward the opposite wall. Holding the applicator at a “snowplow” angle will help maintain a wet edge at all times. **3.** At the end of each run, turn the applicator and pull it toward you through the puddle and pad out the applicator parallel to the wet edge. **4.** Feather out all turns. Do not push too hard or too fast to avoid dripping or splattering. **5.** Missed areas can be touched up if

seen right away. **6.** BE SURE YOU ARE USING THE RECOMMENDED COVERAGE OF 500-600 SQUARE FEET PER GALLON. DO NOT SPREAD TOO THIN. **7.** Allow the first coat to dry 2-3 hours. High humidity and/or low temperature conditions will extend the dry time (recommended conditions of 65-80°F/40-60% relative humidity). **8.** Allow final coat to dry at least 48 hours before use.

**INTERCOAT ABRASION:** It is not necessary to abrade between coats of Bona SuperCourt OPTUM® unless more than 48 hours has passed since the previous coat was applied. For smoothest results, abrade between all coats as necessary with Bona Conditioning Pads or a Bona Multidisc and 240- grit Bona Diamond abrasives.

**CURING:** The curing process takes approximately 7 days, (70% cured in 24 hours, 90% after 72 hours). Do not replace area rugs until the floor has fully cured. The floor may be walked on after 24 hours, but remains susceptible to scuffing or marring until completely cured. No wet cleaning during the first week, only dry dust with a Bona SuperCourt Microfiber Dusting Pad. (Do not use dry dust mop treatment chemicals on wooden floors.)

**FULL SAND AND FINISH PROCESS:** Bona SuperCourt OPTUM® will adhere to most stains, paints, sealers and finishes after proper preparation and dry times. Do not apply Bona SuperCourt OPTUM® to raw wood, or wood flooring in which the surface temperature is below 50°F (10° C). Stain, sealer, paint and finish results may vary widely depending on the wood species, especially on oily and resinous types. ALWAYS PREPARE A SAMPLE OR TEST AREA TO DETERMINE COMPATIBILITY, APPEARANCE AND DESIRED RESULTS. Please follow the Maple Flooring Manufacture Association’s (MFMA) Athletic Maple Floor Resurfacing Specification at [www.maplefloor.org](http://www.maplefloor.org).


### MAINTENANCE:

**CLEAN-UP:** Application tools should be cleaned with water and stored in an airtight container. Recycle container when empty.

**STORAGE:** Nonflammable - Bona SuperCourt OPTUM® should be stored in a climate controlled environment. KEEP FROM FREEZING. Do not store above 100° F (38° C).

**MAINTENANCE:** Place walk-off mats at all entrance doorways to keep out excessive dirt and grit. For best results, see Bona SuperCourt Athletic Floor Care System products for optimal wood floor care.

Technical data	Bona SuperCourt OPTUM®
Certifications	GREENGUARD Gold, Green Seal, MFMA Approved
Color/Form	Milky white
pH	8.5
Scent	Very slight non-offensive odor
Shelf Life	1 year

Product	Pack size	Product code
Bona SuperCourt OPTUM®	5 gallon pail	101100563 

## Safe handling

Please make sure your employees read and understand the product label and Safety Data Sheet before using this product. The label contains directions for use; and both the label and SDS contain hazard warnings, precautionary statements and first aid procedures. SDS are available online at [www.diversey.com](http://www.diversey.com) or by calling 888.352.2249. Improper use or dilution may result in damage to surfaces and may result in health and physical hazards that match those of the concentrate.

GREENGUARD Indoor Air Quality Certified® is a registered certification mark of Air Quality Sciences, Inc.

Green Seal® Certified mark is a registered certification mark owned by Green Seal, Inc.

Bona SuperCourt OPTUM® meets Green Seal® Standard GS-11 based on effective performance, minimized/recycled packaging, and protective limits on VOCs and human toxicity. [GreenSeal.org](http://GreenSeal.org).