

FROGTAPE™ PRO GRADE FLASHING AND WATERPROOFING TAPE

TYPICAL APPLICATIONS

- For exterior deck ledger to house transition
- Also for sealing the following transitions: sill plate, wall to roof, deck to wall joints

PRODUCT FEATURES

- All-weather performance with 12-month UV resistance
- Wide installation temperature range from 0 F (-18 C) to 150 F (65 C) with long-term performance after install in temperatures ranging from -40 F (-40 C) to 240 F (115 C)
- Self-healing around nails and protrusions for a waterproof seal
- Saves time - no primers needed* (*in most applications)
- Features a split release liner for easy removal
- Meets AAMA 711-22

CONSTRUCTION

Backing: 5.0 mils black polyolefin film

Adhesive: 5.0 mils solventless acrylic adhesive

Liner: Moisture stable 2-mil polyester release liner

STANDARD WIDTH

12 in

304.8 mm

STANDARD LENGTH

50 ft

15.3 m

Lead times may apply. Please contact Shurtape customer service for information related to stock and non-stock sizes and colors.

APPLICABLE STANDARDS

AAMA 711-22

STORAGE & USAGE CONDITIONS

Tape should be stored in its original packaging in a cool, dry area away from direct sunlight and should be used within 18 months of date of shipment. Surfaces to which tape is applied should be clean, dry and free of grease, oil and/or other contaminants.

COLOR



PHYSICAL PROPERTIES

	STANDARD	METRIC
Adhesion to Anodized Aluminum	>1.5 lbs/in width	>0.26 N/mm
Adhesion to Exterior Glass Faced Gypsum	>1.5 lbs/in width	>0.26 N/mm
Adhesion to OSB	>1.5 lbs/in width	>0.26 N/mm
Adhesion to Plywood	>1.5 lbs/in width	>0.26 N/mm
Adhesion to Rigid PVC	>1.5 lbs/in width	>0.26 N/mm
Application Temperature Range	0 F to 240 F	-18 C to 116 C
CD Tensile Strength	5.7 lbs/in width	6.57 N/10mm
MD Tensile Strength	16.3 lbs/in width	18.91 N /10mm
Service Temperature Range	-40 F to 240 F	-40 C to 116 C
Thickness - Without Liner	10.0 mils	0.25 mm

Physical and performance characteristics shown above are obtained from tests recommended by PSTC, ASTM, government agencies, or Shurtape Quality Assurance and Technical Service departments and do not represent a guarantee of product performance. Individual rolls may vary from these averages. The user should determine whether the product is fit for a particular purpose and is suitable for the user's method of application before use.

