



# Technical Data Sheet

3M™ Double Coated Tape 9629PC



[Product Details](#)



[Regulatory Info/SDS](#)

## Product Description

Finite Element Analysis (FEA) data is available for this product at: [3m.com/FEA](https://www.3m.com/FEA)

3M™ Double Coated Tapes with 3M™ Quick Bonding Adhesive 360 provides high bond strength to most surfaces, including many low surface energy plastics such as polypropylene and powder coated paints.

## Product Features

- Excellent adhesion to difficult to bond to surfaces such as HDPE, LDPE, and PP.
- Super quick stick.
- Higher adhesion from a thinner tape.
- This tape has a film carrier which can add dimensional stability to foam and other substrates and also make it easier to handle the tape during slitting and die-cutting.

## Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

## Typical Physical Properties

| Attribute Name       | Test Method | Test Condition | Value                           |
|----------------------|-------------|----------------|---------------------------------|
| Adhesive Type        |             |                | Acrylic                         |
| Adhesive Carrier     |             |                | Clear PET (Polyester)           |
| Adhesive Thickness   |             | Faceside       | 0.04 mm (1.75 mil) <sup>1</sup> |
| Carrier Thickness    |             |                | 0.013 mm (0.5 mil)              |
| Adhesive Thickness   |             | Backside       | 0.04 mm (1.75 mil) <sup>2</sup> |
| Total Tape Thickness | ASTM D3652  |                | 0.1 mm (4 mil)                  |
| Liner                |             |                | 58# Polycoated                  |
| Liner Thickness      |             |                | 0.11 mm (4.2 mil)               |
| Primary Liner Color  |             |                | Tan                             |

<sup>1</sup> Faceside adhesive is on the interior of the roll, exposed when unwound and liner removed.

<sup>2</sup> Backside adhesive is on the exterior of the roll, exposed when liner is removed.

## Typical Performance Characteristics

### 180° Peel Adhesion

Temperature: 22 °C (72 °F)

Backing: 2 mil Aluminum Foil

Test Method: ASTM D3330

| Dwell Time | Test Condition | Substrate          | Value                            |
|------------|----------------|--------------------|----------------------------------|
| 30 s       | Faceside       | Polypropylene (PP) | 11 N/cm (105 oz/in) <sup>1</sup> |
| 30 s       | Backside       | Polypropylene (PP) | 13 N/cm (121 oz/in) <sup>1</sup> |
| 15 min     | Faceside       | Polypropylene (PP) | 12 N/cm (109 oz/in) <sup>1</sup> |
| 15 min     | Backside       | Polypropylene (PP) | 15 N/cm (133 oz/in) <sup>1</sup> |
| 72 h       | Faceside       | ABS                | 13 N/cm (121 oz/in) <sup>1</sup> |
| 72 h       | Backside       | ABS                | 14 N/cm (126 oz/in) <sup>1</sup> |

| Dwell Time | Test Condition | Substrate          | Value                            |
|------------|----------------|--------------------|----------------------------------|
| 72 h       | Faceside       | Polycarbonate (PC) | 15 N/cm (133 oz/in) <sup>1</sup> |
| 72 h       | Backside       | Polycarbonate (PC) | 16 N/cm (148 oz/in) <sup>1</sup> |
| 72 h       | Faceside       | Polyethylene (PE)  | 7 N/cm (67 oz/in) <sup>1</sup>   |
| 72 h       | Backside       | Polyethylene (PE)  | 8 N/cm (73 oz/in) <sup>1</sup>   |
| 72 h       | Faceside       | Polypropylene (PP) | 16 N/cm (150 oz/in) <sup>1</sup> |
| 72 h       | Backside       | Polypropylene (PP) | 16 N/cm (143 oz/in) <sup>1</sup> |
| 72 h       | Faceside       | Stainless Steel    | 14 N/cm (129 oz/in) <sup>1</sup> |
| 72 h       | Backside       | Stainless Steel    | 17 N/cm (156 oz/in) <sup>1</sup> |

<sup>1</sup> 12 in/min (300 mm/min)

Temperature: 22 °C (72 °F)

Test Condition: 1000g

| Attribute Name | Test Method | Value                    |
|----------------|-------------|--------------------------|
| Static Shear   | ASTM D3654  | >10,000 min <sup>1</sup> |

<sup>1</sup> 1 in x 1 in sample area, test terminated after 10,000 minutes

| Attribute Name                    | Value                        |
|-----------------------------------|------------------------------|
| Short Term Temperature Resistance | 177 °C (350 °F) <sup>1</sup> |
| Long Term Temperature Resistance  | 93 °C (200 °F) <sup>2</sup>  |

<sup>1</sup> Short Term (minutes, hour)

<sup>2</sup> Long Term (day, weeks)

## Typical Environmental Characteristics

### Environmental Resistance

**Humidity Resistance:**High humidity has minimal effect on adhesive performance. No significant reduction in bond strength is observed after exposure for 72hrs at 150°F (65°C) and 90% relative humidity.

**UV Resistance:**When properly applied, nameplates and decorative trim parts are not adversely affected by exposure.

**Water Resistance:**Immersion in water has no appreciable effect on the bond strength. After 100 hours at room temperature, the high bond strength is maintained.

**Temperature Cycling Resistance:**High bond strength is maintained after cycling six times through:

8 hours at -4°F (-20°C)

8 hours at 150°F (65°C) /90% RH

**Chemical Resistance:**When properly applied, nameplate and decorative trim parts will hold securely after exposure to numerous chemicals including oil, mild acids, and alkalis.

## **Handling/Application Information**

### **Application Examples**

- Foam to powder coated painted surfaces.
- Low surface energy plastic adhesion.

### **Application Techniques**

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application will assist the adhesive in developing intimate contact with the bonding surface.

To obtain optimum adhesion, the bonding surfaces must be clean, dry, and well unified. Typical surface cleaning solvents are methyl ethyl ketone for metals or isopropyl alcohol for plastics.\* Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

\*When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturers precautions and directions for use. These cleaning recommendations may not be compliant with the rules of certain Air Quality Management Districts in California; consult applicable rules before use.

### **Application Equipment**

To apply adhesives in a wide web format, lamination equipment is required to ensure acceptable quality. To learn more about working with pressure-sensitive adhesives please refer to technical bulletin, 3M™ Lamination Techniques for Converters of Laminating Adhesives (70-0704-1430-8).

For additional dispenser information, contact your local 3M sales representative, or the toll free 3M sales assistance number at 1-800-362-3550.

## **Storage and Shelf Life**

Store under normal conditions of 16° to 27°C (60° to 80°F) and 40 to 60% relative humidity in the original packaging, out of direct sunlight. For best performance, use this product within 24 months from date of manufacture.

## **Automotive Disclaimer**

### **Select Automotive Applications:**

This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

## **Information**

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

**Disclaimer:** 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit [www.3M.com](http://www.3M.com).

## **ISO Statement**

This product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M™ Industrial Adhesives and Tapes Division  
3M Center, St. Paul, MN 55144-1000  
3M.com/iatd

3M is a trademark of 3M Company..  
©3M 2024 (6/24)