



A high-quality, urethane wood gym finish with an advanced formulation that dries to a smooth, durable finish. It resists rubber burns and heel marks, plus it repels abrasive dust and dirt for a longer finish life.

**Features & Benefits**

- Advanced formula dries to a smooth, durable finish
- Urethane finish resists rubber burns and heel marks
- Repels abrasive dust and dirt for a longer life
- Light amber color brings out the natural warmth color of the wood.

**Item Number & Unit of Measure**

Item Number	HIL0028507
Unit of Measure	5 gal Pail

**Specifications**

Color	Amber
Appearance	Clear
Fragrance	Solvent
Formula Type	Liquid
Dilution Ratio	RTU
Non-Volatile Matter	40%
Solids Content	40
Coverage SqFt/Gallon	500-600
Dry Time (hrs.)	72

Sheen	Gloss
MFMA Approved	Yes
UL Certified	Yes

**Safety**

See safety datasheet (if applicable) and product label for safety information, handling and proper use.

**Directions for Use**

**SCRUB AND RE-COAT OLD FLOORS:** Scrub with 2 oz./gal. solution of HILLYARD SUPER SHINE-ALL using 120 grit screen discs (250 sq. ft./side of disc) under a single brush floor machine. Pick up the solution with a wet vacuum and damp mop rinse until clean with clean water. Work small areas; do not flood the floor. Allow the floor to dry overnight. Tack the floor with terry cloth towels dampened with HILLYARD TACK-IT. Allow the floor to dry one hour and tack floor a final time using HILLYARD CLEANING CLOTH CHI415 to remove fine dust particles before applying finish. **SCREEN AND RE-COAT OLD FLOORS:** Clean floor with SUPER SHINE-ALL solution; make sure floor is free of soil, polishes, waxes, or oily residues. Abrade the floor using 120 grit screen discs (250 sq. ft./side of disc). Thoroughly vacuum and tack with TACK-IT. Tack floor a final time using CLEANING CLOTH CHI415 to remove fine dust particles before applying finish. Use dust containment precautions and dust masks when dry abrading floor. **PREPARATION: NEW OR FRESHLY SANDED WOOD:** After the floor has been sealed and game lines painted, abrade the floor with maroon pads (250 sq. ft./side of pad). Tack the floor with TACK-IT. Allow floor to dry one hour. Refer to the HILLYARD FIRST IN WOOD GYM FLOOR CARE MANUAL for complete details on care. **APPLICATION:** Before applying GOLD MEDALIST GYM FINISH, tack the floor a final time with CLEANING CLOTH CHI415. Apply finish at a coverage rate of 500-600 sq. ft./gal with a lambswool applicator, HILLYARD MULTI-FLO, E-Z WAY, HILLYARD weighted T-Bar, or approved applicator. Avoid leaving puddles of finish on floor.

If a second coat is to be applied, allow the finish to dry at least 12 hours, abrade entire floor with maroon pads, and tack floor with TACK-IT. If finish dries longer than 48 hours, abrade entire floor with screen discs (150- 100 grit, depending on how long the finish has dried). Apply the final coat. Turn on exhaust/ventilation system 4 hours after each application to promote curing. Do not use floor for 72 hours; wait one week before scheduled activities. **PAINT:** Prior to re- coating, use HILLYARD approved paint following label directions to touch up game lines. Worn areas should be patched with finish prior to re- coating the entire floor. **MAINTENANCE:** Dust mop daily with Hillyard Super Hil-Tone, Hil-Mist, or Hil-Treat. Clean badly soiled floors with Super Shine-All; refer to the Hillyard First in Wood Gym Floor Care Manual for complete details on care. **NOTE:** Best results are obtained with adequate ventilation and floor temperatures above 60 deg.F (16 deg.C) and below 95 deg.F (35 deg.C). Turn on exhaust/ventilation system 2-4 hours after application; avoid direct drafts on floor while finishing. If seal, paints, or finish dry longer than 24 hours after abrasion during the coating process, re- abrade entire floor to ensure proper adhesion of coatings. Do not store partially full containers of material for long periods of time. Do not pour unused material back into container. Empty containers may retain hazardous residue and explosive vapors. Keep away from heat, sparks, and flames. Do not cut, puncture, or weld on or near this container. Follow label warnings until container is thoroughly cleaned or destroyed. **NOTICE: Saw dust from freshly sanded floors or dust from wood floors that have been abraded between coats will spontaneously catch fire if improperly discarded. Immediately after abrading or sanding wood floors, place dust waste in a sealed, water-filled metal container and immediately remove from building. NOTICE: Rags or applicators soaked in a combustible liquid will spontaneously catch fire if improperly discarded. Immediately after using rags or applicators soaked in a combustible liquid,**

**place waste in a sealed, water-filled metal container and immediately remove from building.**