

3M™ Lined Low-Static Polyimide Film Tape 7419L

Product Description

3M™ Lined Low-Static Polyimide Film Tape 7419L uses DuPont™ Kapton® polyimide film backing and acrylic adhesive for printed circuit board solder masking and other high-temperature applications. This is a lined version of 3M™ Low-Static Polyimide Film Tape 7419.

Key Features

- Specially formulated acrylic adhesive is resistant to typical solder mask temperatures for short periods of time. Stays firmly in place during processing and removes cleanly from typical electronic substrates even after 10 minutes @ 260°C (500°F).
- Specially formulated acrylic adhesive formulation does not rely on silicone, which lessens the potential for silicone contamination which can interfere with subsequent bonding or conformal coating operations.
- The high-temperature acrylic adhesive also has excellent chemical resistance and should be considered for demanding chemical masking applications.
- Product is wound on a polyethylene tape core.

3M™ Lined Low-Static Polyimide Film Tape 7419L

	Kapton® Backing: 1 mil
	Acrylic Adhesive: 0.8 mil
	Polyester liner

Product Construction/Material Description

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Lined Low-Static Polyimide Film Tape 7419L	
Property	Value
Adhesive	Specialty Acrylic
Backing	DuPont™ Kapton® Polyimide Film
Color	Amber
Liner	Polyester
Standard roll length	33 meters (36 yards)

3M™ Lined Low-Static Polyimide Film Tape 7419L

Applications

- Masking or protecting residue sensitive areas on printed circuit boards during high-temperature operations such as wave soldering and solder reflow.

Application Techniques

- Substrates should be smooth, clean, dry and oil-free to ensure good wet-out and adequate adhesion.
- Tape may not bond or conform to low surface energy, rough or sharply curved surfaces.

Typical Physical Properties and Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes. Final product specifications and testing methods will be outlined in the products Certificate of Analysis (COA) that is shipped with the commercialized product.

3M™ Lined Low-Static Polyimide Film Tape 7419L		
Property	Test method ^a	Value
Adhesion to stainless Initial 72 hours @ room temp 10 minutes @ 260° C	ASTM D3330, Part A	4 oz/in (4.52 N/100 mm) 5 oz/in (5.65 N/100 mm) 17 oz/in (19 N/100 mm)
Adhesion to copper Initial 72 hours @ room temp 10 minutes @ 260° C	ASTM D3330, Part A	4 oz/in (4.52 N/100 mm) 5 oz/in (5.65 N/100 mm) 10 oz/in (11 N/100 mm)
Backing thickness	ASTM D3652	1.0 mil (0.025 mm)
Total tape thickness	ASTM D3652	1.8 mil (0.046 mm)
Static discharge Removal from roll	3M Test Method	< 180 volts
Dielectric strength	3M Test Method	6000 volts
Surface resistivity	ESD Method S-11	5 x 10 ⁶ ohms/sq
Temperature use range ^{**}	3M Test Method	10 min at 260°C

^aMethods listed as ASTM are tested in accordance with the ASTM method noted

^{**}Static discharge during removal from roll

^{***}Temperature use range is defined as the maximum time at the stated temperature after which the tape may be removed cleanly, without staining, from a copper substrate

Storage and Shelf Life

The shelf life of 3M™ Low Static Polyimide Film Tape 7419 is 18 months from the date of manufacture when stored in the original packaging materials and stored at 21°C (70°F) and 50% relative humidity.

Certificate of Analysis (COA)

The 3M Certificate of Analysis (COA) for this product is established when the product is manufactured and deemed to be commercially available from 3M. The COA contains the 3M specifications, test results and test methods for the product's performance attributes that the product will be supplied against. Contact your local 3M representative for this product's COA.

3M™ Lined Low-Static Polyimide Film Tape 7419L

Technical Information: The technical information, recommendations, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating this 3M product and determining whether it is appropriate and suitable for user's application.

Warranty Disclaimer: This 3M product is sold or made available "AS IS." **3M MAKES NO WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE.**

Limitation of Liability: Except to the extent prohibited by applicable law, 3M will not be liable for any loss or damage arising from or related to this 3M product, whether direct, indirect, special, incidental, or consequential, regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: For industrial use only. Not intended, labeled or packaged for consumer sale or use.



Electronics Materials Solutions Division
3M Center, Building 223-3S-32
St. Paul, MN 55144-1000
1-800-251-8634 phone
651-778-4244 fax
www.3M.com/electronics

DuPont and Kapton are trademarks of E.I. du Pont de Nemours and Company or its affiliates.

3M is a trademark of 3M Company.
Please recycle.

©3M 2025. All rights reserved.
60-5005-0026-3