

Medium Duty Reinforced WAT

3-way fiberglass reinforced natural kraft carton sealing tape manufactured with water-activated adhesive available in Natural, Snowwhite and Superwhite.

PRODUCT APPLICATION

Used for two strip sealing cartons top and bottom. Works well on recycled cartons, and non-unitized loads.

ADHESION

(WATER AT RECOMMENDED 110°F/43°C)

FIPAGO	
2/0	44
2/1	66
5/0	70
15/0	86
MCLAURIN	
	86

STORAGE RECOMMENDATION

Store new stock behind current stock. Store in a clean, dry place. Temperature of 70°F (21°C) +/- 6°F, and 40% to 50% relative humidity are recommended.

SHELF LIFE

When stored under recommended conditions, converted rolls have an expected shelf life of up to two years from date of shipment. Jumbo rolls have the same expected shelf life, but it is recommended that they are converted within 6 months of date of shipment.

CUSTOMER SERVICE: 800.474.8273
TAPE TECHNICAL SERVICE: 877.447.4832
INSIDE SALES: 888.898.7834 | INFO@ITAPE.COM

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.



NOMINAL VALUES

The following data are nominal values based on ASTM and other standard tests. This data should not be considered specification.

PHYSICAL PROPERTIES

Caliper	7
MD Tensile ASTM 33650	83
CD Tensile ASTM 33650	30

Recommended for use on average weight cartons up to 55 pounds (25 kg).

CONSTRUCTION PER SQUARE

TOP PLY ASTM 33650	25 lb (41 g/m ²) Natural Kraft Paper
BOTTOM PLY ASTM 33650	25 lb (41 g/m ²) Natural Kraft Paper
LAMINATING ADHESIVE	Hot Melt
WATER-ACTIVATED ADHESIVE	Modified Starch
MD REINFORCEMENT	(2-1-1-1-2) 75 Fiberglass (per 3"), ½" spacing
CD REINFORCEMENT	(1-1-1) 150 Fiberglass, 1.10" spacing, 43 degree angle