

Reinforced Water-Activated Tape

Natural Kraft, reinforced, light duty, economy grade, Water-Activated Carton Sealing Tape, manufactured with a starch based adhesive. Venom has fiberglass reinforcement in the machine direction and polyester reinforcement in the cross direction.

Used for two strip sealing cartons top and bottom. Works well on recycled cartons, and non-unitized loads. Recommended for use on cartons w/ average weight up to 20 pounds (9 kg).

PRODUCT APPLICATION

ADHESION

(WATER AT RECOMMENDED 110°F/43°C)

FIPAGO	
2/0	45 mm-kgf
2/1	63 mm-kgf
5/0	65 mm-kgf
15/0	81 mm-kgf
MCLAURIN	
	83

CUSTOMER SERVICE: 800.474.8273
 TAPE TECHNICAL SERVICE: 877.447.4832
 INSIDE SALES: 888.898.7834 | INFO@ITAPE.COM

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.



NOMINAL VALUES

The following data are nominal values based on ASTM and other standard tests. This data should not be considered specification.

PHYSICAL PROPERTIES

Caliper	6.2 mils (0.2 mm)
MD Tensile ASTM 33650	55 lb (240.8 N/25mm)
CD Tensile ASTM 33650	23 lb (100.7 N/25mm)

CONSTRUCTION PER SQUARE

TOP PLY ASTM 33650	20 lb (33 g/m2) Natural Kraft Paper (virgin fibers)
BOTTOM PLY ASTM 33650	23 lb (37 g/m2) Natural Kraft Paper (virgin fibers)
LAMINATING ADHESIVE	High Melt Index Polypropylene Base Blend
WATER-ACTIVATED ADHESIVE	Synthetically Modified Starch
MD REINFORCEMENT	(1-1-1) per 70mm (1-1-1-1/1-1-1-1) per 72mm 110 Fiberglass
CD REINFORCEMENT	(1-1-1) Polyester 1.10" spacing, at 44° angle