



# Technical Data Sheet

## 3M™ Screen Printable Polyester Performance Durable Label Material 7034



Additional Info



Regulatory  
Info/SDS

### **Product Description**

3M™ Screen Printable Polyester Performance Durable Label Materials are durable, high performance materials that offer thermal stability and moisture resistance. These topcoated polyester label stocks utilize 3M™ Adhesive P1400 which is a high performance tackified acrylic designed for use in demanding environments, including outdoor applications.

### **Product Features**

- UL Recognized file MH16411, CSA Group Certified file 99316
- Adhesive offers UV resistance and adhesion to a wide variety of substrates, including polyolefins.
- Liner provides easy sheet processing and is designed for the ultimate in layflat. The backside of this liner is not printable.

### **Technical Information Note**

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

### **Typical Physical Properties**

| Attribute Name       | Value                            |
|----------------------|----------------------------------|
| Adhesive Type        | P1400 Perm.                      |
| Facestock            | White Polyester TC               |
| Adhesive Coat Weight | 1.6 — 1.96 g/100 in <sup>2</sup> |

| Attribute Name      | Value   |
|---------------------|---|
| Adhesive Thickness  | 0.023 mm (0.9 mil)  |
| Facestock Thickness | 0.05 mm (2 mil)   |
| Liner               | 90# Polycytd. bleached kraft sheet polyethylene coated on two sides |
| Liner Thickness     | 0.18 mm (7 mil)   |

| Attribute Name | Value   |
|----------------|---|
| Convertability | 3M™ Outdoor Acrylic Adhesive P1400 is specifically designed to be compatible with a variety of print methods and end use applications. Adhesive processing issues are not anticipated when proper roll tensions, handling and storage conditions are used. Please refer to the die cutting/converting section of this data page or the “Guide to Converting and Handling Label Products” technical bulletin for additional information. |

## Construction Tested

Adhesion properties determined per TLMI Method using 1.0 mil polyester with 1.0 mil of adhesive on a polished stainless steel panel.

## Typical Performance Characteristics

### 180° Peel Adhesion

Temperature: 23 °C (73 °F)

Test Method: TLMI

| Substrate                        | Value                             |
|----------------------------------|-----------------------------------|
| High Density Polyethylene (HDPE) | 2.62 N/cm (24 oz/in) <sup>1</sup> |
| Polycarbonate (PC)               | 6.12 N/cm (56 oz/in) <sup>1</sup> |
| Polypropylene (PP)               | 5.28 N/cm (48 oz/in) <sup>1</sup> |
| Stainless Steel                  | 7.04 N/cm <sup>1</sup>            |

<sup>1</sup> 300 mm/min (12 in/min)

Test Method: TLMI

| Attribute Name | Temperature   | Value                                      |
|----------------|---------------|--|
| Liner Release  | 23 °C (73 °F) | 3 – 39 g/cm (15 – 200 g/2 in) <sup>1</sup> |
| Shear Adhesion |               | 4 h <sup>2</sup>                           |
| Loop Tack      |               | 3.16 N/cm (28.8 oz/in) <sup>3</sup>        |

<sup>1</sup> 180° removal, 300 in/min

<sup>2</sup> 0.25 in<sup>2</sup> x 500g

<sup>3</sup> 300 mm/min (12 in/min)

| Attribute Name                           | Value                        |
|--|------------------------------|
| Application Temperature                  | 5 – 49 °C (40 – 120 °F)      |
| Long Term Temperature Resistance         | 150 °C (302 °F) <sup>1</sup> |
| Minimum Long Term Temperature Resistance | -29 °C (-20 °F) <sup>1</sup> |

<sup>1</sup> Long Term (day, weeks)

| Attribute Name | Value                       |
|----------------|-----------------------------|
| Note           | Calipers are nominal values |

## Printing

High gloss general purpose topcoating is designed for use with UV, solvent and water-based screen inks. Topcoating will also accept flexo, ion deposition, off set, letter press, hot stamp, and thermal transfer printing. The converter should verify that their ink systems are compatible with the topcoating on the polyester film by testing beforehand. Ink systems recommended for testing are listed below.

### UV Screen Inks: Solvent Screen Inks:

ANI Printing Inks (formerly Nazdar's Akzo Nobel) Uvoscreen II 7700 and System 2  
Environmental UV III Screen Pro Sericol's Polyplast PY, GVYL, VYL, TMI and Techmark  
Nazdar 1600  
Sericol's Uviflex, 021 UV, UV and PEL

Water-based Screen Inks: Water-based Flexo Inks:  
Nazdar 2700 ANI Printing Inks Hydro Film 4000 Series  
Arcar Ultra Film Series 5 Inks

## Converting

Die cut with steel rule or flatbed dies. The 90# lay-flat liner also allows kiss cutting and back splitting. The converter can cut through the polyester facestock without cutting through the liner. Sheet label materials are not recommended for rotary die cutting and stripping operations.

## **Handling/Application Information**

### **Application Examples**

- Nameplates and product ID labels.
- Rating plates.
- Property identification and asset labeling.
- Warning, instruction, and service labels for durable goods, equipment/machinery and lawn and garden.

### **Application Techniques**

For maximum bond strength, the surface should be clean and dry. Typical cleaning solvents are heptane and isopropyl alcohol.\*

For best bonding conditions, application surface should be at room temperature or higher. Low temperature surfaces, below 40°F (5°C) can cause the adhesive to become so firm that it will not develop maximum contact with the substrate. Higher initial bonds can be achieved through increased rubdown pressure.

\*When using solvents, read and follow the manufacturer's precautions and directions for use.

## **Industry Specifications**

UL Recognized, File PGJ12.MH16411, Printing Materials - Component, ANSI/UL 969  
CSA Group Certified, File 99316, Class 7922, Adhesive-Type Labels - Label Stock, CSA-C22.2 No. 0.15-15 Update No. 1

## **Storage and Shelf Life**

Store under normal conditions of 16° to 27°C (60° to 80°F) and 40 to 60% relative humidity in the original packaging, out of direct sunlight. For best performance, use this product within 24 months from date of manufacture.

## **Available Sizes**

| <b>Attribute Name</b> | <b>Value</b>                                      |
|-----------------------|---|
| Packaging             | Finished labels should be stored in plastic bags. |

## **Information**

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

**Disclaimer:** 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit [www.3M.com](http://www.3M.com).

## **ISO Statement**

This product was manufactured under a 3M quality system registered to ISO 9001 standards.