

Processing Procedure Artesano Luxury Bath Rugs

PROCESSING REQUIREMENTS

Formula: This formula is only a guideline. Alterations should be made at the discretion of the laundry professional based on specific requirements, supplies, equipment, and experience.

	OPERATION	TIME	WATER LEVEL	TEMP.	SUPPLIES
1.	Flush	3 min.	High	100°F	--
2.	Break/Suds	8-12 min.	Low	160°F	Nonionic detergent/Alkali
3.	Bleach	6 min.	Low	150°F	Sodium Hypochlorite*
4.	Rinse	2 min.	High	135°F	--
5.	Rinse	2 min.	High	120°F	--
6.	Rinse	2 min.	High	105°F	--
7.	Sour	5 min.	Low	90°F	Sour to a pH of 5.5-6.5

DRYING

After washing, tumble dry at a maximum temperature of 160°F. Do not over dry.

* The use of chlorine bleach must be carefully controlled and completely rinsed from these items to ensure the long-term colorfastness of colored rugs. Peroxide bleaching or the use of an anti-chlor is recommended for situations that require “safer” processing because of control limitations.

Mild bleaching of white rugs is recommended to maintain white appearance.