







AMERICAN OLEAN®

FINISHES: MATTE | POLISHED

















SPECIAL FEATURES



















NOT APPLICABLE FOR ALL PRODUCTS IN THIS SERIES. SEE CHARTS FOR FULL PRODUCT DETAILS.

MARBLE LOOK

FLOOR TILE

SUMMIT FY02







CONTRAST FY03



STEELY FY04

3" LANDMARK HEXAGON MOSAIC



SUMMIT FY02



CONTRAST FY03



3" HEXAGON MOSAIC







CONTRAST FY03



STEELY FY04

















AMERICAN OLEAN®

FINISHES: MATTE | POLISHED

USAGE













PRICING



SPECIAL FEATURES

















NOT APPLICABLE FOR ALL PRODUCTS IN THIS SERIES. SEE CHARTS FOR FULL PRODUCT DETAILS.

MARBLE LOOK

SIZES

		THICKNESS	SQ. FT./ CARTON	PIECES/ CARTON
24 x 48 Floor Tile	23-3/8" x 46-7/8" (59.44 cm x 119.20 cm)	5/16"	15.26	2
12 x 24 Floor Tile	11-5/8" x 23-3/8" (29.56 cm x 59.44 cm)	5/16"	17.02	9
3" Hexagon Mosaic* (Mesh-mounted)	12-1/8" x 14-5/8" Sheet (30.80 cm x 37.15 cm Sheet)	5/16"	6.24	6
3" Landmark Hexagon Mosaic** (Mesh-mounted)	17" x 11-1/2" Sheet (43.18 cm x 29.21 cm Sheet)	5/16"	4.92	6

- * 3" Hexagon Mosaic available in Matte finish only.
- ** 3" Landmark Hexagon Mosaic available in Polished finish only.

APPLICATIONS

	TARGET DCOF WET	SUITABLE
Dry & Level – Interior Floor	N/A	•
Wet & Level – Interior Floor	≥ 0.42	•*
Shower Floors (Residential or Light Commercial)	≥ 0.42	•**
Exterior Floor Applications (including patios, pool decking & other wet areas with minimal footwear)	≥ 0.60	
Ramps & Inclines	≥ 0.65	
Walls/Backsplashes	N/A	•
Countertops	N/A	•
Pool Linings	N/A	***

A DCOF value of ≥ 0.42 is the standard for tiles specified for level interior spaces expected to be walked upon when wet, as stated in ANSI A137.1-A326.3. For more information about DCOF and the DCOF AcuTest $^{\text{IM}}$, visit americanolean.com/DCOF.

APPLICATION NOTES:

Suitable for exterior applications (provided it is noted as suitable in the applications chart above) in freezing and non-freezing climates, when proper installation methods are followed.

- * Matte finish only.
- ** 3" Hexagon Mosaic only.
- *** Mosaic tile only.

FEATURES



PRE-CONSUMER RECYCLED MATERIALS



MADE IN THE U.S.A



REVEAL IMAGING®







All or select items within this series meet the requirements for these qualifications. For more information visit americanolean.com

TRIM

		NUMBER	PIECES/ CARTON
Floor Bullnose	3 x 24	P43F9	10

INSTALLATION

irout Joint Recommendation	Shade Variation
Floor: 1/8" (3/16" when multiple sizes are installed in a modular pattern, and/ or when installing tile with a length 15" or greater in a staggered brick-joint pattern; overlap should not exceed 33%.)	-
Mosaic: 1/8"	RANDOM (V4)

PERFORMANCE CHARACTERISTICS

	ASTM#	RESULTS
Water Absorption	C373	< 0.5%
Breaking Strength	C648	> 275 lbs.
Scratch Hardness	MOHS	8.0 (Matte) 6.0 (Polished)
Chemical Resistance	C650	Resistant

For additional information on test results, visit us at: americanolean.com/information/TestResults.

DURABILITY

Floor Surface Wear Resistance

1	Residential Bathrooms	3	All Residential / Light Commercial
2	All Residential Areas	4	All Residential / Commercial

NOTES

Since there are variations in all fired ceramic and natural products, tile and trim supplied for yo particular installation may not match samples. Final confirmation should be made from actual tiles and trim prior to installation. Manufactured in accordance with ANSI A137.1 standards.

Not for use on ramps. Water, oil, grease, improper drainage and certain footwear can create slippery conditions. Floor applications expected to be exposed to these conditions require extra caution in product selection.

For additional information refer to "Factors to Consider" at: americanolean.com/Factors.

Random visuals enhance the natural beauty of this product. To achieve optimal results, all tile should be selected from multiple cartons and shading and graphic arrangement planned prior to installation.

 $Special \ consideration \ needs \ to \ be \ given \ when \ installing \ tiles \ greater \ than \ 15 \ inches. \ Please \ refer \ to$ americanolean.com/LargeTiles for more information.

 $Manufacturer\ Advisory:\ All\ tile\ is\ measured\ by\ the\ DCOF\ AcuTest^{\text{\scriptsize{TM}}}\ method.\ Tiles\ with\ DCOF\ values$ $<\!0.42\,are\,not\,recommended\,for\,use\,in\,areas\,with\,wet\,or\,slippery\,conditions.\,For\,more\,information, see$ ANSI standard A137.1 section 6.2.2.1.10, available at www.tileusa.com.

Special care should be taken when grouting with dark pigmented colors. A grout release is recommended to prevent finely powdered pigments from lodging in the pores of the surface. Use of a latex modified thin-set is recommended for installation.



