













8,00 mm / COLOURED BODY PORCELAIN STONEWARE

| | Reference standard E.N. 14411-ISO 13006 . Appendix G. Group Bla. GL | Test method | Reference value | Declared value |
|---|--|-------------|--|--------------------------|
|  | Water absorption | ASTM-C373 | ≤0.5% | ≤ 0.4% |
|  | Stain Resistance | ASTM-C1378 | Surfaces are exposed to staining agents for 24 hours followed by four cleaning procedures. Results are recorded post cleaning. | CLASS A |
|  | Stain Resistance | ASTM-C1378 | Surfaces are exposed to staining agents for 24 hours followed by four cleaning procedures. Results are recorded post cleaning. | NOT AFFECTED |
|  | Breaking strength | ASTM-C648 | ≥250 lb/ft ² | ≥ 300 lb/ft ² |
|  | Resistance to freeze | ASTM-C1026 | A tile sample is subjected to repeated processes of freezing and thawing. Sample must show no visible defects. | RESISTANT |
|  | Warpage edge (rectified) | ASTM-C485 | Warpage ± 0.4% or ± 0.05 in | ≥ ± 0.4% |
|  | Warpage diagonal (rectified) | ASTM-C485 | Warpage ± 0.4% or ± 0.07 in | ≥ ± 0.4% |
|  | Warpage edge (pressed) | ASTM-C485 | Warpage ± 0.5% or ± 0.07 in | ≥ ± 0.5% |
|  | Warpage diagonal (pressed) | ASTM-C485 | Warpage ± 0.5% or ± 0.07 in | ≥ ± 0.5% |
|  | Wedging | ASTM-C502 | ± 0.25% or ± 0.03 in | ≥ ± 0.25% |
|  | Thickness | ASTM-C499 | Range: ± 0.04 in | ≤ 0.04 in |
|  | Chemical resistance | ASTM-650 | A tile sample is placed in continuous contact with a variety of chemicals for 24 hours. No sample must show visible defects. | NOT AFFECTED |



≥0.42% wet

ANSI-A326.3

≥0.42% wet

≥ 0.42% wet

Copyright © 2013 Florim S.p.A. SB a socio unico.
Sede Legale: Via Canaletto 24, 41042 Fiorano Modenese.
Reg. Imprese di Modena Nr. 01265320364.
Capitale Sociale i.v. Euro 50.000.000 P/CF 01265320364