

KEATON CERAMIC TILE




KEATON CERAMIC TILE




3' x 10' KEATON IVORY CERAMIC BULLNOSE
56-059



3' x 13' KEATON IVORY CERAMIC BULLNOSE
46-178




10' x 16' KEATON IVORY CERAMIC WALL TILE
56-058



13' x 13' KEATON IVORY CERAMIC FLOOR TILE
46-177



8' x 10' KEATON IVORY CERAMIC
WALL TILE 52-194



2' x 2' KEATON IVORY MOSAICS
46-181


KEATON CERAMIC TILE




3' x 10' KEATON ICE CERAMIC BULLNOSE
56-055



3' x 13' KEATON ICE CERAMIC BULLNOSE
46-174




10' x 16' KEATON ICE CERAMIC WALL TILE
56-054



13' x 13' KEATON ICE CERAMIC FLOOR TILE
46-173



8' x 10' KEATON ICE CERAMIC WALL
TILE 52-192



2' x 2' KEATON ICE MOSAICS
46-179

KEATON CERAMIC TILE




3" x 10" KEATON CARBON CERAMIC BULLNOSE
56-057



3" x 13" KEATON CARBON CERAMIC BULLNOSE
46-176



10" x 16" KEATON CARBON CERAMIC WALL
TILE 56-056



13" x 13" KEATON CARBON CERAMIC FLOOR TILE
46-175



8" x 10" KEATON CARBON CERAMIC
WALL TILE 52-193



2" x 2" KEATON CARBON MOSAICS
46-180

KEATON CERAMIC TILE

PACKAGING INFORMATION

DESCRIPTION	ITEM CODE			LBS/BOX	PCS/BOX	SQFT/BOX	BOXES/SKID	SQFT/SKID
	IVORY	ICE	CARBON					
13" x 13" KEATON CERAMIC FLOOR TILE	46-177	46-173	46-175	43.83	11	12.91	58	748.90
8" x 10" KEATON CERAMIC WALL TILE	52-194	52-192	52-193	27.42	20	10.76	92	989.92
10" x 16" KEATON CERAMIC WALL TILE	56-058	56-054	56-056	42.15	14	15.06	48	723.07
2" x 2" KEATON MOSAICS	46-181	46-179	46-180	37.00	10	11.74	48	563.52
3" x 13" KEATON CERAMIC BULLNOSE	46-178	46-174	46-176	21.00	21	N/A	84	1764 pcs.
3" x 10" KEATON CERAMIC BULLNOSE	56-059	56-055	56-057	15.00	25	N/A	98	2450 pcs.

GENERAL SPECIFICATIONS

DESCRIPTION	METHOD	UNIT	13" x 13"
THICKNESS		mm – in	7.6 mm – 5/16"
WATER ABSORPTION	EN ISO 10545-3	(%)	≤ 3
ABRASION RESISTANCE	EN ISO 10545-7	(PEI)	4
SCRATCH HARDNESS		(Mohs)	6
BREAKING STRENGTH	EN ISO 10545-4	(lbf)	≥ 250
CHEMICAL RESISTANCE	EN ISO 10545-13	(GL)	Class A – Resistant
FROST RESISTANCE	EN ISO 10545-12		Resistant
STATIC COEFFICIENT OF FRICTION (WET)	ASTM C-1028	(μ)	< 0.60
STATIC COEFFICIENT OF FRICTION (DRY)	ASTM C-1028	(μ)	≥ 0.90
DCOF (WET)	ANSI B101.3		< 0.42
SHADE VARIATION			V1