

BELLINA CERAMIC TILE



BELLINA CERAMIC TILE



3" x 13" BELLINA GREY BULLNOSE
4002-0003-0



3" x 10" BELLINA GREY BULLNOSE
4002-0005-0




13" x 13" BELLINA GREY FLOOR TILE
4000-0005-0



10" x 16" BELLINA GREY WALL TILE
4000-0003-0



3" x 8" BELLINA GREY BULLNOSE
4002-0004-0




8" x 10" BELLINA GREY WALL TILE
4000-0001-0



2" x 2" BELLINA MULTI MOSAICS
4001-0000-0

BELLINA CERAMIC TILE



3" x 13" BELLINA CREAM BULLNOSE
4002-0000-0



3" x 10" BELLINA CREAM BULLNOSE
4002-0002-0



13" x 13" BELLINA CREAM FLOOR TILE
4000-0004-0



10" x 16" BELLINA CREAM WALL TILE
4000-0002-0



3" x 8" BELLINA CREAM BULLNOSE
4002-0001-0



8" x 10" BELLINA CREAM WALL TILE
4000-0000-0

BELLINA CERAMIC TILE

PACKAGING INFORMATION

DESCRIPTION	LBS/BOX	PCS/BOX	SQFT/BOX	BOXES/SKID	SQFT/SKID
8" x 10" BELLINA WALL TILE	26.28	20	10.76	92	989.92
10" x 16" BELLINA WALL TILE	30.89	10	10.76	72	774.72
13" x 13" BELLINA FLOOR TILE	44.19	11	12.91	58	748.90
3" x 8" BELLINA BULLNOSE	12.81	30	n/a	105	3150 pcs.
3" x 10" BELLINA BULLNOSE	15.62	25	n/a	98	2450 pcs.
3" x 13" BELLINA BULLNOSE	20.83	21	n/a	84	1764 pcs.
2" x 2" BELLINA MULTI MOSAICS	39.33	10	11.74	48	563.52

GENERAL SPECIFICATIONS

DESCRIPTION	METHOD	UNIT	13" x 13"
THICKNESS		mm – in	7.6 mm – 5/16"
WATER ABSORPTION	EN ISO 10545-3	(%)	≤ 3
ABRASION RESISTANCE	EN ISO 10545-7	(PEI)	3
SCRATCH HARDNESS		(Mohs)	5
BREAKING STRENGTH	EN ISO 10545-4	(lbf)	≥ 250
CHEMICAL RESISTANCE	EN ISO 10545-13	(GL)	Class A – Resistant
FROST RESISTANCE	EN ISO 10545-12		Resistant
STATIC COEFFICIENT OF FRICTION (WET)	ASTM C-1028	(μ)	< 0.60
STATIC COEFFICIENT OF FRICTION (DRY)	ASTM C-1028	(μ)	≥ 0.90
DCOF (WET)	ANSI B101.3		< 0.42
SHADE VARIATION			V2