

3M™ Electrically Conductive Double-Sided Tape 9793KT Series

Product Description

3M™ Electrically Conductive Double-Sided Tape 9793KT Series is XYZ electrically conductive pressure sensitive adhesive (PSA) tape. 3M tape 9793KT series consists of CPSA and a porous conductive matrix and is used as a PSA attachment to the grounding surface. The product is an acrylic based adhesive solution and offers adhesion and grounding performance to many surface types. 3M tape 9793KT series provides electrical grounding performance with small contact areas and PSA attachment for EMI shielding designs.

Key Features

- Conductive foam carrier layer
- Conformable CPSA design
- EMI Shielding
- Grounding capabilities
- High adhesion properties
- Available in multiple thickness variations

3M™ Electrically Conductive Double-Sided Tape 9793KT Series

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.



Product Construction / Materials Descriptions

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Electrically Conductive Double-Sided Tape 9793KT Series*	
Color	Face Side: Grey metallic Back Side: Grey metallic
Conductive Adhesive Type	Acrylic Adhesive Conductive Foam Matrix
Release Liner**	Face Side: Transparent PET release liner Back Side: Transparent PET release liner

Note: *The product is available in 1050 mm x 100 meters. Contact your local 3M representative for more information.

3M™ Electrically Conductive Double-Sided Tape 9793KT Series

Typical Physical Properties and Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes. Final product specifications and testing methods will be outlined in the product's Certificate of Analysis (COA) that is shipped with the commercialized product.

3M™ Electrically Conductive Double-Sided Tape 9793KT Series											
Property	Target Value										Test Method
9793KT-XXX	9793KT - 130	9793KT - 150	9793KT - 180	9793KT - 210	9793KT - 230	9793KT - 255	9793KT - 300	9793KT - 350	9793KT - 400	9793KT - 500	
Thickness (µm)	130	150	180	210	230	255	300	350	400	500	ASTM D1000 ^a
Adhesion to SUS Face Side (gf/inch)	1000	1800	1800	2000	2000	2000	2500	2500	2500	2500	ASTM D1000 ^a
Adhesion to SUS Back Side (gf/inch)	1000	1800	1800	2000	2000	2000	2500	2500	2500	2500	ASTM D1000 ^a
Electrical Resistance through Z-Axis	0.01 ~ 0.25 Ω										3M ETM-12 ^b

^a Tested in accordance with ASTM D1000 test method.

^b 3M test method notes attached.

Shielding Effectiveness

Many factors determine the shielding effectiveness of a conductive adhesive tape, including type and thickness of the conductive layers, adhesive strength, degree of contact, smoothness of application surface, test frequency, etc. For 3M™ Electrically Conductive Double-Sided Tape 9793KT Series, the typical shielding effectiveness is expected to be in the range of 40 dB to 60 dB, using a standard EMI shielding test methods and through the thickness of the sample tested.

Applications

3M tape 9793KT series is typically used for applications requiring excellent electrical conductivity from the application substrate through the adhesive to a second substrate. Common uses include grounding and EMI shielding in equipment, and electronic components.

Application Techniques

Note: Carefully read and follow the manufacturer's precautions and directions for use when working with solvents. Tape application below 10°C (50°F) is not suggested. Once properly applied, low temperature holding power is generally satisfactory.

The bond strength of 3M tape 9793KT series depends on the amount of adhesive-to-surface contact developed during application, substrate type and surface conditions.


- 1) Firm application pressure helps develop better wet-out and adhesive contact and may lead to improved bond strength as well as electrical conductivity. Pressure must be applied to the bond area after assembly to help ensure sufficient wet-out of the 3M tape 9793KT series adhesive to the substrates and to engage the conductive acrylic adhesive fillers with the substrates to make electrical connection. Mechanical pressure (roller, metal bar) or finger pressure at 5-15 psi. (Optimally the application conditions are determined via a set of Design of Experiments (DOE) using a range of application pressures, dwell time and temperatures (suggested initial range might include 5-15 psi, 2-5 seconds, 21°C-38°C).
- 2) Heat may be applied simultaneously with pressure to improve wetting, final bond strength and electrical conductivity. Suggested temperature range to evaluate is in the 38°C-60°C range.

3M™ Electrically Conductive Double-Sided Tape 9793KT Series

- 3) To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Some typical surface cleaning solvents are isopropyl alcohol or heptane.


3M ETM-7: XY-Axis Electrical Resistance through Adhesive

Place a strip of the single (double) side conductive tape in 10 mm x 50 mm with adhesive side down between the electrodes on 3M ETM-7 testing board. After initial hand lamination to provide for a 10 mm x 10 mm contact area between the tape and electrodes, apply a 2kg rubber roller across the tape one time. Application method simulates a typical manufacturing process that might be used to apply the tapes to a surface. After 20 minutes of dwell time, the DC resistance, between the electrodes, is measured with a micro-ohm meter. The resistance results are recorded after 5 ~ 30 seconds for initial resistance.



3M ETM-12: Z-Axis Electrical Resistance through Adhesive

Place conductive tape pieces in 10 mm x 10 mm on the center of the electrodes on 3M ETM-7 testing board. Then place 3M ETM-12 testing board with the gold-plated side down on the tapes between electrodes. After initial hand lamination to provide for a 10 mm x 10 mm contact area between the tapes and electrodes, apply 2kg rubber roller across the tape one time. Application method simulates a typical manufacturing process that might be used to apply the tapes to a surface. After 20 minutes of dwell time, the DC resistance, between the electrodes, is measured with a micro-ohm meter. The resistance results are recorded after 5 ~ 30 seconds for initial resistance.



3M™ Electrically Conductive Double-Sided Tape 9793KT Series

Storage and Shelf Life

The shelf life of 3M™ Electrically Conductive Double-Sided Tape 9793KT Series is 12 months from the date of manufacture when stored in roll form, in the original packaging materials, and stored at 10°C-25°C (50°F-77°F) and <60% relative humidity.

Once the tape is removed from the original packaging materials, the tape should be converted, shipped and stored in the prescribed temperature and humidity-controlled conditions to ensure stable tape performance. Adhesion, tack, conductivity and reliability of the tape in an application can be reduced if the tape is not controlled to the prescribed handling and usage conditions.

In addition, in some applications the tape may be converted (die cut, laminated to other materials or release/processing liners) in such a manner that the release liner that the product tape is shipped with is removed and a different release or processing/carrier liner is applied to the adhesive side of the tape. The new release/carrier liner may transfer release agents (silicone, fluoropolymer, etc.) to the tape's adhesive surface and thus reduce the applied tack and/or adhesion strength of the tape in the end user's application to a surface versus when no release/carrier liner changes have occurred. Any proposed release/carrier liners to be used with the tape should be tested with the tape to ensure that the tape's performance is not negatively impacted for the intended end use application and that shelf life is not negatively impacted. If a poor performing liner is selected for a liner exchange, it can have a significant negative impact on the conductive tape's adhesion/tack/electrical performance and/or significantly reduce shelf life.

Certificate of Analysis (COA)

The 3M Certificate of Analysis (COA) for this product is established when the product is manufactured and is deemed commercially available from 3M. The COA contains the 3M specifications, test methods and test results for the product's performance attributes that the product will be supplied against. Contact your local 3M representative for this product's COA.

This technical data sheet may contain preliminary data and may not match the COA specification limits and/or test methods that may be used for COA purposes.

3M™ Electrically Conductive Double-Sided Tape 9793KT Series

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product in accordance with all applicable instructions and with appropriate safety equipment, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specifications on the Certificate of Analysis, which is established when the product is manufactured and deemed commercially available and is provided at the time 3M ships the product. **3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE.** If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement or repair of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by applicable law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: For industrial use only. Not intended, labeled or packaged for consumer sale or use.



3M Display & Electronics

3M Center, Building 223-3S-32
St. Paul, MN 55144-1000 U.S.A.

Phone 1-800-3M HELPS
Web 3M.com/Electronics

3M is a trademark of 3M Company.
All other trademarks herein are the
property of their respective owners.
©3M 2026. All rights reserved.
60-5005-0454-7