













## 10,00 mm / COLOURED BODY PORCELAIN STONEWARE

	Reference standard E.N. 14411-ISO 13006 . Appendix G. Group Bla. GL	Test method	Reference value	Declared value
	Chemical resistance	ASTM-650	A tile sample is placed in continuous contact with a variety of chemicals for 24 hours. No sample must show visible defects.	NOT AFFECTED
	Resistance to freeze	ASTM-C1026	A tile sample is subjected to repeated processes of freezing and thawing. Sample must show no visible defects.	RESISTANT
	Stain Resistance	ASTM-C1378	Surfaces are exposed to staining agents for 24 hours followed by four cleaning procedures. Results are recorded post cleaning.	NOT AFFECTED
	Water absorption	ASTM-C373	≤0.5%	≤0.4%
	Breaking strength	ASTM-C648	≥250 lb/ft <sup>2</sup>	≥ 400 lb/ft <sup>2</sup>
	≥0.42% wet	ANSI-A326.3	≥0.42% wet	≥ 0.42% wet
	Warpage edge (rectified)	ASTM-C485	Warpage ± 0.4% or ± 0.05 in	≥ ± 0.4%
	Warpage diagonal (rectified)	ASTM-C485	Warpage ± 0.4% or ± 0.07 in	≥ ± 0.4%
	Warpage edge (pressed)	ASTM-C485	Warpage ± 0.5% or ± 0.07 in	≥ ± 0.5%
	Warpage diagonal (pressed)	ASTM-C485	Warpage ± 0.5% or ± 0.07 in	≥ ± 0.5%
	Wedging	ASTM-C502	± 0.25% or ± 0.03 in	≥ ± 0.25%
	Thickness	ASTM-C499	Range: ± 0.04 in	≤0.04 in

