













## 10,00 mm / GLAZED PORCELAIN STONEWARE

Reference standard E.N. 14411-ISO 13006 . Appendix G. Group Bla. GL		Test method	Reference value	Declared value
	Water absorption	ASTM-C373	$\leq 0.5\%$	$\leq 0.4\%$
	Chemical resistance	ASTM-650	A tile sample is placed in continuous contact with a variety of chemicals for 24 hours. No sample must show visible defects.	NOT AFFECTED
	Stain Resistance	ASTM-C1378	Surfaces are exposed to staining agents for 24 hours followed by four cleaning procedures. Results are recorded post cleaning	NOT AFFECTED
	Breaking strength	ASTM-C648	$\geq 250$ lb/ft <sup>2</sup>	$\geq 400$ lb/ft <sup>2</sup>
	Resistance to freeze	ASTM-C1026	A tile sample is subjected to repeated processes of freezing and thawing. Sample must show no visible defects.	RESISTANT
	$\geq 0.42\%$ wet	ANSI-A326.3	$\geq 0.42\%$ wet	$\geq 0.42\%$ wet
	Warpage edge (rectified)	ASTM-C485	Warpage $\pm 0.5\%$ or $\pm 0.07$ in	$\geq \pm 0.4\%$
	Warpage diagonal (rectified)	ASTM-C485	Warpage $\pm 0.5\%$ or $\pm 0.07$ in	$\geq \pm 0.4\%$
	Warpage edge (pressed)	ASTM-C485	Warpage $\pm 0.4\%$ or $\pm 0.05$ in	$\geq \pm 0.5\%$
	Warpage diagonal (pressed)	ASTM-C485	Warpage $\pm 0.4\%$ or $\pm 0.07$ in	$\geq \pm 0.5\%$
	Wedging	ASTM-C502	$\pm 0.25\%$ or $\pm 0.03$ in	$\geq \pm 0.25\%$
	Thickness	ASTM-C499	Range: $\pm 0.04$ in	$\leq 0.04$ in

