

Processing Procedure Colored Stripe Pool Towel

PROCESSING REQUIREMENTS

Formula: This formula is only a guideline. Alterations should be made at the discretion of the laundry professional based on specific requirements, supplies, equipment and experience.

<u>OPERATION</u>	<u>TIME</u>	<u>WATER LEVEL</u>	<u>TEMP.</u>	<u>SUPPLIES PER 100 LB. LOAD</u>
1. Flush	3 min.	High	100°F	---
2. Break	6 min.	Low	160°F	8 oz. nonionic detergent & 16 oz. alkali
3. Suds	6 min.	Low	160°F	4 oz. nonionic detergent
4. *Bleach	5 min.	Low	160°F	1 qt. 1% sodium hypochlorite
5. Rinse	2 min.	High	145°F	---
6. Rinse	2 min.	High	130°F	---
8. Sour/ **Softeners	5 min.	Low	100°F	Sour to pH of 5.5 - 6.5

*The use of chlorine needs to be controlled to ensure long term colorfastness.

Since pool towels typically contain residual pool chemicals that could have an affect on the wash chemistry, the use of an anti-chlor in the wash process should be considered.

**Softeners are recommended to maintain a soft hand, avoid overuse as they can have a negative affect on the absorbency performance.

DRYING

Tumble dry at 160°F until dry and use an appropriate cool down cycle.

Do not over-dry; hems should be "slightly" damp at the end of the drying cycle.

Do not overload as the product should float freely in the dryer.

Please contact the Technical Affairs Department of Standard Textile for any additional information at 1-800-999-0400.