



# 205 Series

## CONSTRUCTION SHEATHING TAPE



### DESCRIPTION

This tape is made of a UV resistant polypropylene film and coated with high shear, high tack solvent based acrylic adhesive.

*\* This tape is meant for permanent application only. It will leave adhesive residue if removed.*

### MAIN FEATURES

- High tack adhesive provides aggressive contact.
- Strong and durable holding power.
- Water and moisture resistant.
- Excellent resistance to UV and weathering.
- Prevents air infiltration.
- CCMC Evaluation Report #11955-R.

### APPLICATIONS

- Sealing of joints and seams of sheathing membranes.
- Tape has to be pressed firmly on surface.
- Should be applied on clean, dry surfaces.

### TECHNICAL DATA

|   |   |
|---|---|
| Colour .....                                  | Red (02), White (10)                                    |
| Backing .....                                 | UV Resistant Polypropylene Film                         |
| Adhesive .....                                | Solvent Based Acrylic                                   |
| Thickness .....                               | 3 mil   |
| Adhesion to steel .....                       | 40 oz/in  |
| Tensile strength .....                        | 30 lb/in  |
| Elongation .....                              | 120%  |
| Application Temperature .....                 | -10°C (14°F) to 50°C (122°F)                            |
| Temperature Resistance .....                  | -40°C (-40°F) to 100°C (212°F)                          |
| VOC (Volatile Organic Compound) content ..... | Estimated 0,1%  |
| Water Vapor Transmission (ASTM E96) .....     | 0.068 perm (gr/ft <sup>2</sup> /hr/in-Hg)               |
| Water Penetration Rate (ASTM D3816) .....     | 0.05 g/100 in <sup>2</sup> /24 hr                       |
| Air Permeance Rate (ASTM E2178) .....         | 0.0010 L/s m <sup>2</sup> [0.0002 cfm/ft <sup>2</sup> ] |

**STRONG HOLDING POWER**

**HIGH TACK ADHESIVE**

#### Please note:

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness.

The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded.

No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

