# Silverside

### Colors



White



Driftwood



Tan





Ash



Medium Gray





### Size

7" x 48" x 3mm - Luxury Vinyl Tile

- White •
- Ash •
- Light Gray • Driftwood •
- Medium Gray •
- . Charcoal



Light Gray







Khaki

- Tan •
  - - Taupe . Khaki •
    - Brown •

### SILVERSIDE



#### **Product Features**

### Technical Data

TOGUCTICAL	0105		100	
Construction	Dimensions	Plank: 7" x 47.98"		
	Overall Thickness	3mm	Overall	
	Wear Layer Thickness	20 mils		
	Raw Material	100% Virgin Vinyl	Wear-I	
	Edge Detail	4-Sided Square Edge	Dimen	
	Surface	Ceramic Bead with Anti-bacterial finish	Square	
Installation Method:	Glue Down		Residu	
Recommended Adhesive	TEC Flexera	Bostik LVT-Lock+ Bostik Multi-Lock	Flexibi	
	TEC Flexera HT	Bostik Uni-Lock	Dimen	
Warranty	10 Year Commercial / Lifetime Residential warranty		Curling	
Country of Origin	South Korea	Chemi		
	1			



Scan for additional product details



TEST ITEM	STANDARD	TEST METHOD	REQUIREMENTS	RESULTS
Overall thickness		ASTM F386	Nominal ±0.005in	Meets
Wear-layer thickness		ASTM F410	0.020 in (0.5mm) minimum For Commercial use	Meets
Dimension	ASTM F1700	ASTM F2055	±0.016 in. per linear foot	Meets
Squareness		ASTM F2055	Maximum 0.010 in (0.25mm)	Meets
Residual indention		ASTM F1914	Average less than 8%	Meets
Flexibility		ASTM F137	1-in (25.4 mm) mandrel No crack, No damage	Meets
Dimension stability		ASTM F2199	0.020 in/lin-ft maximum	Meets
Curling after exposure to heat	EN ISO 10582	EN ISO 23999	±2mm (+0.5mm / -1mm)	Meets
Chemical resistance		ASTM F925	No more than a slight change in surface dulling, surface attack, or staining	Meets
Resistance to light	ASTM F1700	ASTM F1515	⊿ E < 8 ave MAX	Meets
Resistance to heat		ASTM F1514	⊿ E < 8 ave MAX	Meets
Fire resistance - CRF		ASTM E648	Class 1 (0.45 w/Cm 2 or more)	Meets
Fire resistance (smoke density)		ASTM E662	450 or less	Meets
Static load limit		ASTM F970	0.005 in or less	2,000 psi
Indoor air quality	CDPH v1.2 (2017) a.k.a CHPS 01350		Low VOC	Floorscore Certified
Slip resistance		ASTM D2047		Pass (Dry .61, Wet .72)

## Request samples.

www.vitlsurfaces.com samples@vitlsurfaces.con





